MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KY-788 LOT 34863

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
50	67	3,350		
	STUMP			

TOTAL NET WT. 3,350 PKG. N-CODE 1130

PROD. SPVR. 2PP DATE 3/ 1 WHSE. OPER.

22
240

CG 03 CODE KY-788-D PKG. ____

→ MAR13 34863

EST. WGT. ~~960~~ 860 LBS.

OK
AP

O.K
BAGS
3460

Total Wgt. ~~3560~~# Req(____)

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-788-D (J)	EWK 9/22/76
	DCG 9/27/76
TYPED BY-	
NE 2/17/77	

MAKING NOTES

REMARKS

NAME: "KROLOR" YELLOW - LIGHT NON-BLEEDING

INSTRUCTIONS 240

VAT			
DATE	3-13-80		
TIME	7:25AM		
RELEASED BY	GG		
PRESS	22	23	24
NO. OF CAKES	46	46	46

PRESS With AGITATION
WASH TO 2000 OHMS with 35-75°F water
TEST AFTER 2 HOURS
LOAD on 6 cars

SAMPLES 1- 8oz JAR
DELIVER TO CTL for Color

-PRESSING- RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	8am				
CAKES USED	46				
WATER ON	12:30 PM				
HRS. WASHED	5				
OHMS	2500				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION	7				
NO. CARS LOADED					

EXPLAIN LOSSES

SAMPLED BY WH69 RELEASED BY AK

-DRYING-

1- Dry 12 hrs at 220 °F L.V. M.V.
Then Dry 8 hrs at 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATED
No Record of any Processing Loss.

ADDITIONAL DRYING HOURS REQUIRED

No. Drums 15

SAMPLES
DELIVER TO

NO. CARS PULLED LUMP WGT. 3336
SAMPLED BY RELEASED BY BLL

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING
SAMPLES 1 Env. & 1 Pt can
DELIVER TO C T L

DATE MIXED
SAMPLED BY RELEASED BY

DUP050094690

.00 T

3486.3 #
.41 #
294 #
.00 T

2.56
.14 -
2.42
.14 -
2.50
.14 -
2.35
.14 -
2.42
.14 -
2.45
.14 -
2.51
.14 -
2.53
.14 -
2.56
.14 -
2.44
.14 -
2.46
.14 -
2.41
.14 -
2.37
.14 -
2.28
.14 -
1.20
.14 -
33.36 T

DUP050094691