



ASBESTOS

RW

Inter Office

Manufacturing Staff

July 25, 1980

Messrs. N. Abu-Nassar
D. T. Axon
P. S. Dewar
A. G. Folger
W. S. Hulse

F. J. Kallin
J. D. Kindree
D. J. McChesney
P. E. Toth ✓

PLAINTIFF'S EXHIBIT

FD-1459

Subject: Current Trends in Regulation of Asbestos and
Availability of Asbestos Substitutes
June 14-16, 1980, Washington, D.C.

Attached for your information and file is a summary of the Environmental
Protection Agency (EPA) and Consumer Product Safety Commission (CPSC)
meeting on asbestos usage.

T. A. Loch

TAL/gw
Att.

8005 1083

PRODUCED BY FORD

SCF-ALLF-08200

REPORT OF CONTACT

Subject: EPA/CPSC/IRLG Information-Gathering Meeting
in Advance of Rule-Making
to Regulate the Usage of Asbestos

Date and Place: June 14-16, 1980
Washington, D.C.

Purpose

The National Institute for Occupational Safety and Health (NIOSH) has recommended to the Occupational Safety and Health Administration (OSHA) that the current asbestos exposure limit of 2 fibers per cubic centimeter (fibers/cc) be reduced to 0.1 fibers/cc in recognition of the carcinogenicity of asbestos fiber. This move is part of a coordinated effort to systematically remove asbestos from all materials where substitutes are available. The Interagency Regulatory Liason Group (IRLG) is seeking to unify the regulatory efforts of OSHA, the Environmental Protection Agency (EPA), and the Consumer Product Safety Commission (CPSC) in determining the state of the art in cost effective asbestos substitutes which do not impose the long-term potential health hazards characteristic of asbestos fiber.

The meeting consisted of presentations and roundtable discussions among representatives of the asbestos industry, government regulatory officials, asbestos substitute material vendors and their technical representatives, and members of those industries who are present consumers of asbestos containing materials.

Specific Applications

While Manufacturing Staff has been designated to evaluate the cost-effective asbestos-substitute materials presently available for Companywide applications, one current specific interest involves the use of asbestos-cement (A/C) sheet for building construction.

The available substitutes for A/C sheet include: glass-reinforced concrete (GRC); cement/wood board; cement-based materials using reinforcing fibers made from mineralized wood, steel, mineral wool, carbon, nylon, or ceramics. Tables I and II list the unit costs associated with currently available substitutes.

TABLE I - COMPARISON OF CEMENT SHEET PRODUCT PRICES

Product	Cost (\$) per square meter (square foot)	
	1/4"	1/2"
J. M. Flexboard (A/C)	5.90 (0.55)	14.00 (1.30)
J-M Transite (A/C)	13.15 (1.20)	21.50 (2.00)
Cement/wood board	1.95 (0.20)	4.00 (0.40)
High density GRC	-	8.61 (0.80)
Low density GRC	-	less than 8.60 (0.80)
Alumina-Sheet	161.40 (15.00)	-

8005 1084

TABLE II - COMPARISON OF SIDING PRODUCT COSTS

Product	Total cost (\$) per square meter (square foot)
Wood siding, 5/8"	8.60 (0.80)
Wood shingle	15.60 (1.45) ^a
Asbestos-cement shingle	13.50 (1.25) ^a
Fiber board	10.80 (1.00) ^a
Brick or stone	61.75 (5.75) ^a
Stucco or concrete block	17.90 (1.65) ^a
Aluminum	13.40 (1.25) ^a

^aCost includes material price for plywood sheathing of \$2.72/square meter (\$0.253 square feet).

At the conference, asbestos industry representatives disputed the accuracy of the unit prices presented above. EPA/CPSC acknowledged possible errors and intends to update the information and distribute the data to attendees.

Deficiencies in the performance/weatherability of substitute materials were cited by asbestos manufacturers. In particular, cement/wood board, which had been used widely in Europe as an asbestos substitute, tends to gain and lose moisture in wood fibers causing cracking. Despite these deficiencies, EPA/CPSC assert that the above materials are cost effective asbestos substitutes for current use of A/C sheet.

Additional Information

Other items on the agenda included a diversity of subjects such as: asbestos regulatory status update; overview of non-asbestos substitutes for friction products, paper products, gaskets and packings, plastics and flooring, textiles, roofing materials and sealants, asbestos cement sheet building materials, and asbestos cement pipe; roundtable discussions on the general development of asbestos substitutes and market acceptance of these new materials; overview of health aspects related to the use of new asbestos substitutes which are fibrous in their morphology and are either synthetically manufactured or are naturally occurring.

This symposium's proceedings were tape recorded by EPA for subsequent publication. That record will, in part, form the basis for a technical and economic feasibility assessment related to the eventual ban of asbestos in those applications where substitutes are already available. The EPA is slated to publish an Advanced Notice of Proposed Rulemaking in April, 1981 with the Notice of Proposed Rulemaking (which establishes a near term date of enforcement/compliance) due in August, 1982. The issues raised at the meeting clearly demonstrated that EPA's/CPSC's economic assessments distributed at the meeting were in serious question and that substantial revisions have to be made based on information yet to be supplied by industry representatives present.

8005 1085

PRODUCED BY FORD

Other salient points are as follows:

- . The symposium provided a marketing forum for asbestos substitute material vendors and did not appear to be conducive to unbiased presentation of factual information.
- . EPA/CPSC asserts that cost-effective, proven asbestos substitutes are already on the market and proliferation of these materials requires only consumer/industry education.
- . The general philosophy expressed by CPSC is one which seeks to eliminate asbestos usage without regard for the tendency of asbestos fibers in various products to become airborne.

Background information presented at the meeting is attached. EPA intends to publish a summary of the symposium which will also contain reprints of the papers presented. Estimated time to publication is three months.



T. A. Loch

Attachments
TAL/so/7-22

8005 1086

PRODUCED BY FORD

Toxic Substances



Background Information on Substitutes for Asbestos

Sponsored by:

The Environmental Protection Agency

The Consumer Product Safety
Commission

The Interagency Regulatory Liason
Group

Four sets of parallel diagonal stripes, each consisting of a thick black stripe and two thinner white stripes, arranged horizontally across the bottom of the page.

8005 1087

PRODUCED BY FORD

PREFACE

This document presents background information on substitutes for asbestos, for use by attendees at the Workshop on Substitutes for Asbestos, sponsored by the Environmental Protection Agency, the Consumer Product Safety Commission, and the Interagency Regulatory Liaison Group. The information is the result of a preliminary study of substitutes for asbestos by EPA; data on the special qualities of asbestos-containing products, the available substitute materials, and cost comparisons between asbestos and the substitute materials are presented. This report is being distributed in order to form a basis for discussion of substitutes by participants at the workshop. Comments on the accuracy and validity of the report as well as any additional information are welcomed. Cost data were obtained from a variety of sources and though they are believed to portray 1979 values, the EPA cannot guarantee their accuracy.

CONTENTS

1.	Introduction.	1
2.	Paper Products.	2
	Beverage and pharmaceutical filters.	2
	Millboard.	2
	Commercial papers.	4
	Specialty papers.	4
	Roofing felt.	4
	Beater-add gaskets.	5
	Electrical insulation.	5
	Flooring felt.	5
	Pipeline wrap.	5
3.	Asbestos-Cement Pipe.	6
4.	Floor Tiles and Sheeting.	8
5.	Friction Materials.	9
6.	Sealants.	10
7.	Asbestos/Cement Sheet.	11
8.	Gaskets and Packings.	13
9.	Reinforced Plastics.	17
10.	Textiles.	19
	Fire-resistant materials.	19
	Thermal insulation.	19
	Electrical insulation.	19
	Packings and gaskets.	19
	Friction materials.	19
	Specialty textiles.	20
11.	Miscellaneous.	25
	Drilling muds.	25
	Other products.	26
12.	Conclusions.	27
13.	References.	29

SECTION 1

INTRODUCTION

Asbestos is the common name for a group of fibrous silicates including chrysotile, amosite, anthophyllite, crocidolite, and tremolite-actinolite. Asbestos is used in many industrial and consumer products to provide strength, heat resistance, corrosion resistance, rot resistance, and fireproofing. The United States currently uses approximately 7 pounds of asbestos per person in products each year. An approximate breakdown for the major product categories is:

● Asbestos paper (including commercial roofing)	38 percent*
● Asbestos cement pipe	16 percent
● Floor tile	13 percent
● Friction products	7 percent
● Sealants	7 percent
● Asbestos cement sheet	6 percent
● Gaskets and packing	3 percent
● Plastics, textile, and miscellaneous	10 percent

This document summarizes the present information on the special qualities of asbestos-containing products, the available substitute materials, and cost comparisons between asbestos and the substitute materials.

*Percent of annual United States asbestos consumption. Clifton, R.A. Mineral Industry Survey, Asbestos Industry 1978. U.S. Bureau of Mines, August 22, 1979.

SECTION 2

PAPER PRODUCTS

Asbestos-containing paper can be used in products that serve many different functions. The performance and availability of substitute products will vary for each asbestos-paper product; therefore, this section presents the following subcategories of paper products:

- Beverage and Pharmaceutical Filters
- Millboard
- Commercial Papers
- Specialty Papers
- Roofing Felt
- Beater-Add Gaskets
- Electrical Insulation
- Flooring Felt
- Pipeline Wrap

Table 1 presents the estimated current annual consumption of asbestos fiber in paper products.

BEVERAGE AND PHARMACEUTICAL FILTERS

Asbestos is used in filters because of its large surface area per unit of weight and natural positive charge, which facilitates the removal of negatively charged particles from beverages.¹ Asbestos filter sheets are primarily used by the beer, wine, and liquor distilling industries to filter micro-organisms and very fine solids from liquids and to act as a clarifier removing haze from the liquid medium.

Substitute filters, composed of cellulose fibers, diatomaceous earth and a melamine resin, appear to be adequate alternatives to asbestos filters, although, instead of a natural positive charge, they must be chemically treated to produce a positive charge. Costs are comparable for both the asbestos and substitute filters.

MILLBOARD

Asbestos millboard resists rot and supplies protection from fire, heat, and corrosion. Asbestos millboard is used as a fire-resistant lining in floors, partitions, ceilings, and fire doors, and as an insulating barrier in stove ovens, and heating appliances. It has important uses in metal and chemical industries as well, due to the high temperature performance requirements.

**TABLE 1. ESTIMATED CURRENT ANNUAL CONSUMPTION
OF ASBESTOS FIBER IN PAPER PRODUCTS
(IN TONS) 2,3,4**

Category	Consumption
Flooring felt	130,000
Roofing felt	90,000
Beater-add gaskets	30,000
Pipeline wrap	20,000
Millboard	8,000
Electrical insulation	1,000
Commercial paper	
General insulation	3,500
Muffler paper	NA
Corrugated paper	NA
Specialty papers	
Cooling tower fill	2,500
Transmission paper	1,000
Chlorine electrolytic diaphragms	3,500
Decorative laminates	NA
Beverage and pharmaceutical filters	100
Total paper products	286,100*

* Total should be increased slightly to include subcategories without figures.

NA - Not available but considered small.

Substitute millboard is primarily composed of an alumina-silicate refractory material. Substitute products generally have equal or superior insulating qualities relative to asbestos board, but most have significantly higher costs (see Table 2).

TABLE 2. COST(\$) PER SQUARE FOOT FOR ASBESTOS MILLBOARD AND SUBSTITUTE PRODUCTS⁵⁻⁷

Thickness (inches)	Asbestos	Pars No. 9	Johns-Manville ^a Ceraform 102	Carborundum Fiberfrax		
				Duraboard	Hotboard ^a	GC Board ^b
1/8	\$0.30	\$0.85	\$1.00	—	—	—
1/4	\$0.60	\$1.45	\$1.20	—	—	\$3.10
1/2	\$1.15	\$2.80	\$1.65	\$2.20	\$1.30	—

^aPrice for 1,000 square feet or more.

^bPrice for 75 square foot lots.

COMMERCIAL PAPERS

Asbestos is used in commercial papers because of its strength, durability, and resistance to fire and corrosion. Commercial asbestos papers, including general insulation paper, muffler paper, and corrugated paper, provide maximum insulation against fire, heat, and corrosion with minimum product thickness.

Substitutes are made from ceramics, cellulose, or fiberglass. These materials display some advantages, such as the ability to withstand a greater temperature range, but they cost more and provide less dimensional stability.

SPECIALTY PAPERS

Asbestos is used in specialty papers, including cooling tower fill, electrolytic diaphragms, and decorative laminates, primarily because of its chemical and heat resistant properties.

Substitutes for cooling tower fill are polyvinyl and polypropylene plastics, cellulose, aluminum, and steel. An alternative to asbestos electrolytic diaphragms is a membrane-cell, consisting of a film of perfluoro-sulfuric acid resin and another monomer to which negative sulfuric acid groups are attached. Glass and ceramic substrates are available as substitutes for decorative laminates. Generally, costs for these substitute materials are higher than asbestos-containing papers.

ROOFING FELT

Roofing felt, primarily used for built-up roofing and as an underlayment for other roofing products, is manufactured with asbestos because of its dimensional stability and resistance to rot, fire, and heat. There are three substitutes for asbestos roofing felt: organic felt (cellulosic fibers), fiberglass felt, and a single-ply membrane system (a laminate of a modified bitumen or rubber and plastic or PVC). Organic felt is the most widely used roofing felt, followed by asbestos felt; fiberglass felt holds the smallest share of the roofing market. Table 3 provides a cost comparison of roofing felts. The substitutes for asbestos containing roofing products are currently available and are fairly comparable in costs when installed, durability and performance.⁸

TABLE 3. ROOFING COSTS⁹⁻¹³

	Retail cost per roll (\$)	Squares	Single square (one layer) (\$)	Material cost per square (\$)	Installed cost per square (\$)	
					Range	Average
Organic felt	10.00	4	2.50	7.50 (three layers)	100-160	126.00
Asbestos felt	23.50	4	5.75	11.50 (two layers)	115-160	132.50
Fiberglass felt	28.50	5	5.60	16.80 (three layers)	110-160	140.00
Membrane single-ply	35.70	1	35.70	35.70 (one layer)	—	150.00

BEATER-ADD GASKETS

Gaskets are installed to provide tight, nonleaking connections in piping and other joints. They are used in the automotive industry, and also in industrial and commercial equipment of all varieties. Asbestos is used in gaskets because it is heat resistant, resilient, strong, and chemically inert.

Although alternative materials may be available for certain applications, there are no substitute products of the same effectiveness. In particular, no suitable substitutes have been found for applications requiring the chemical inertness and oil resistance of asbestos gasketing material.⁸ The alternative materials that are sometimes employed are ceramic fibers, teflon, and metal. The costs of these substitute materials are generally higher than the asbestos containing materials.

ELECTRICAL INSULATION

The largest use of asbestos electrical paper is as insulation for dry transformers for layer insulation, layer barriers, core barrier tubes, general conductor wraps, lead insulation, and cross-over insulation. Asbestos is used in electrical paper insulation because of its high thermal and electrical resistance, which permits the paper to act effectively as an insulator and protects the conductor from fire.

Substitute materials currently available for electrical insulation are aromatic polyimides, ceramic fibers, mica, and glass fiber. The costs of these substitutes are higher than the asbestos-containing materials.

FLOORING FELT

Most flooring felt is used commercially in residential applications. Asbestos is used in flooring felts to add dimensional stability, and high moisture, rot and heat resistance. There has been little success in substituting other fibers for asbestos fibers in this product.⁸ Alternatively, various floor coverings can be used as substitutes for vinyl sheet flooring backed with asbestos felt. These coverings include everything from foam cushion-backed flooring and hockless sheet flooring to wood flooring or carpeting and "place and push" vinyl tile squares. Costs of substitute products vary widely as the substitutes themselves differ greatly.

PIPELINE WRAP

Asbestos paper has been successful as pipeline wrap because asbestos can resist soil chemicals, rotting, and decay, while maintaining dimensional stability throughout its lifetime. Asbestos pipe wrap protects underground pipelines from corrosion. The largest user of asbestos pipe wraps is the oil and gas industry with their extensive underground piping networks.

Alternatives to asbestos pipewrap include saturated fiberglass, plastic tapes, extruded epoxy resins and extruded polyethylene wrapping, bound to undercoating.¹⁴ Cost effectiveness still favors asbestos pipe wraps and, although competitive pipeline wraps are also used by the oil and gas industry, asbestos wraps are currently preferred because of cost and proven effectiveness.

SECTION 3

ASBESTOS-CEMENT PIPE

Asbestos-cement (A/C) pipe is most suitable for intermediate range pipe diameters (6 to 24 inches). A/C pipe is strong, resilient, flexible, durable, inert, and fire resistant. The majority of A/C pipe produced is used for water mains (pressure pipe) and sewer lines (nonpressure pipe).

A 1974 survey projected the total amount of water mains in use in the United States to be about 640,000 miles.¹⁵ A/C pipe accounted for 84,000 miles or about 13 percent of this total. Table 4 lists the types of water main pipe in place as of 1975 and the national projections of mileage. Table 5 lists the type of sewer main pipe now in place and the national projections of mileage.

TABLE 4. TYPES OF WATER MAIN PIPE IN PLACE (1975) NATIONAL PROJECTIONS OF MILEAGE¹⁵

	Cast iron	Asbestos cement	Steel	Reinforced concrete	Plastic	Other	Total
Total Mileage	482,000	84,000	38,000	10,000	7,000	19,000	640,000
Percent of Total	75.3	13.1	5.9	1.6	1.1	3.0	100.8

NOTE: Cast iron is the predominate type of pipe now in place, accounting for three-fourths of the total. Asbestos cement has a 13 percent share with none of the other types having more than 6 percent.

TABLE 5. TYPE OF SEWER MAIN PIPE NOW IN PLACE-NATIONAL PROJECTIONS OF MILEAGE¹⁵

	Cast iron	Asbestos cement	Vitrified clay	Reinforced concrete	Plastic	Other	Total
Total Mileage	15,000	25,000	306,000	74,000	10,000	28,000	459,000
Percent of Total	3.3	5.4	66.8	16.2	2.1	6.2	100.0

NOTE: Vitrified clay is the predominate type of pipe now in place, accounting for two-thirds of the total. Reinforced concrete has a 16 percent share with none of the other types having more than 6 percent of the total. The majority of pipe within the "other" category is of the unreinforced concrete category.

The common pipe products available as substitutes for A/C pipe include:

- Ductile iron pipe
- Concrete pipe
- Glass-reinforced concrete pipe
- Plastic pipe
- Vitrified clay pipe

8005 1095

None of these products alone could substitute for all A/C pipe uses. However, as a group, they can meet all of the technical requirements placed on A/C pipe. A/C pipe used in water mains can be replaced by ductile iron, PVC, and reinforced concrete. In sewer mains, A/C pipe can be replaced with vitrified clay, concrete, PVC, and ductile iron. The only factor preventing the use of substitutes for A/C pipe in new construction or replacement service is economics. Table 6 lists pipe price estimates for asbestos cement and the substitute materials.

TABLE 6. PIPE PRICE ESTIMATES 16-21

Material	Approximate price per foot (\$)					
	Water			Sewer		
	8"	15"	24"	8"	15"	24"
Asbestos cement	5.50	16.00 (16")	—	3.00	10-14.00	25-30.00
Ductile iron	6.00	14.50 (16")	24.50	6.00	14.50 (16")	24.50
Vitrified clay	—	—	—	2.50	10.00	29.00
Reinforced concrete	—	—	15.50	—	6.00	11.50
Nonreinforced concrete	—	10.50	—	2.25	4.00	8.00
PVC	4.25	9.75 (12")	—	2.75	10.50	16.00 (18")
Fiber reinforced PVC*	6.25	12.25 (12")	—	—	—	—

*Johns-Manville - Permastrain

SECTION 4

FLOOR TILES AND SHEETING

Vinyl asbestos (V/A) flooring is installed in industrial, commercial, institutional, and residential buildings because it is extremely well suited to applications requiring:

- Toughness
- Dimensional stability
- Long life
- Economy
- Moisture resistance
- Smooth surface
- Cleanability

In 1975 asbestos flooring commanded a 91 percent share of the resilient floor covering market.²² Of this total 38 percent was floor tile and 53 percent was sheet flooring. Only 9 percent of the resilient floor covering market was held by nonasbestos-containing products.

Major V/A flooring companies are actively pursuing or producing a substitute flooring product. Available alternate flooring products include vinyl-sheet roll goods, solid vinyl floor tiles, ceramic tile, carpeting, and wood.⁶ However, these substitutes lack one or more of the above-mentioned characteristics of V/A flooring. The primary hindrances to a substitute product effectively competing with V/A flooring are higher cost and lack of toughness; i/e., durability, resilience, flexibility, and wear resistance.

SECTION 5

FRICITION MATERIALS

Asbestos is well suited for use in friction materials because of its thermal stability, reinforcing abilities, and relatively high ability to withstand friction. Asbestos-containing friction materials are used for brakes for light- and heavy-duty vehicles, aircraft, railcars, various types of heavy equipment and clutch facings.

Several manufacturers of friction materials have active research and testing programs to develop asbestos-free materials. Although industry's research and development activities are highly secretive, we know that among the materials proposed in the past as substitutes are: glass fiber, steel wool, mineral wool, carbon fiber, cermet (sintered metals), semimetallic materials, potassium titanate fibers, aramid fibers, vermiculite, and silicon nitrides. Some firms may have ceased research on one or more of these materials but others may still be under consideration.

Several manufacturers of friction materials have active research and testing programs to develop asbestos-free materials. Some of the materials proposed as substitutes are: glass fiber, steel wool, mineral wool, carbon fiber, cermet (sintered metals), semimetallic materials, potassium titanate fibers, aramid fibers, vermiculite, and silicon nitrides.

As friction applications vary, so do the materials most appropriate for each use. Semimetallic and cermet materials may all be used in direct asbestos substitute applications, semimetallic in disc brakes (it is projected that in 5 years nearly all original equipment disc brakes in passenger cars and light trucks will use semimetallics) and cermets for aircraft brakes (95 percent of all new commercial aircraft use cermets).^{23,24} Nonasbestos drum brake linings for passenger cars are currently unavailable commercially.²³

A cost comparison for various materials proposed as substitutes for asbestos in friction products is given in Table 7.

TABLE 7. COSTS OF MATERIALS PROPOSED AS
SUBSTITUTES FOR ASBESTOS IN
FRICITION MATERIALS²⁵

Material	Price per pound (\$)
Asbestos	0.05-0.15
Fibrous glass	0.05-0.75
Mineral wool	0.15
Potassium titanate fibers	1.00-1.25
Graphite and carbon fibers	10.00-12.00
Wollastonite	0.15
Cotton linters	0.15
Aramid fibers	6.00-8.00

Exact costs for semimetallic friction materials are not available, but they are comparable to organic friction materials. Cermets cost three to five times as much as asbestos friction materials.

SECTION 6

PAINTS, COATINGS, AND SEALANTS

Asbestos is used in asphalt and tar bases for products such as roof sealants, waterproof coatings, and automobile undercoatings. Previous uses of asbestos in texture paints, spackle, and joint compounds have been banned. The asbestos fiber serves as a filler and reinforcing agent in these diverse products.

An acceptable substitute must be:

- Noncombustible
- Resistant to decay, many acids, and vermin
- Made up of long, flexible fibers
- Strong enough to reinforce other binders
- Unaffected by temperatures up to 500°C (automobile undercoating)
- Cost effective

There are no substitutes available that possess all the above attributes, but for applications where several of the characteristics are not necessary, a substitute may be applicable.

There are no commercially available asbestos-free, asphalt-based roofing, undercoating, or linings and chemical resistant coatings products that provide the properties of asphalt-based products. However, several companies report the availability of products in the premarket or early commercial stages. 26,27 For nonasphalt asbestos-based linings and chemically resistant coatings, several mineral reinforcing materials are available as substitutes for asbestos. Although use of asbestos in texture paints was banned in 1977, no substitutes of comparable quality have been found.

Table 8 presents a cost comparison for substitute materials used in sealant products.

TABLE 8. COST OF SUBSTITUTE MATERIALS COMPARED WITH GRADE 7 CHRYSOTILE ²²

Substitute	Cost (\$/pound)	Substitute	Cost (\$/pound)
Chrysotile	0.06-0.12	Barite	-
Fiberglass	0.40-0.50	Diatomite	-
Polypropylene	0.35	Silica	-
Cellulose	0.60	Clay	0.04-0.08
Cotton	0.20	Mica	0.05
Talc	0.06	Carbonate	0.04-0.08
		Nylon	0.60

SECTION 7

ASBESTOS/CEMENT SHEET

Asbestos is used as a reinforcing material in cement sheet products because of its high tensile strength, flexibility, resistance to heat, chemical inertness, and large aspect ratio. Asbestos fiber in cement sheet adds to the stability, strength, stiffness, and toughness of the material, resulting in a product that is rigid; durable; noncombustible; and resistant to heat, weather, and attack by corrosive chemicals. A/C sheet may be broken down into four product categories: flat sheet, corrugated sheet, siding shingles, and roofing shingles.

Asbestos can be replaced in A/C sheet by either a substitute reinforcing fiber or an entirely different sheet material. Glass-reinforced concrete (GRC) appears to be suitable for most corrosion and heat resistant applications where A/C sheet is currently used.²⁸ Cement/wood board, once it is actually under production, should be a cheaper material than A/C sheet for general construction purposes.²⁹ No substitute material is available that adequately matches A/C sheet's qualities as a laboratory table top; nor is there a material available that could replace ebonized A/C sheet in all electrical applications.

Table 9 presents the performance of possible fiber substitutes for asbestos in cement sheet.

TABLE 9. PERFORMANCE OF POSSIBLE FIBER SUBSTITUTES FOR ASBESTOS IN CEMENT SHEETS

Fiber	Performance and Comments	Reference
Alkali-resistant glass	Can be used in Portland cement; better impact resistance than asbestos; product loses strength with time; commercially feasible.	22,30
Mineralized wood	Lightweight; not as heat resistant as asbestos; superior impact resistance, abundant supply available; commercially competitive.	29
Steel fibers	Good enforcement; high impact strength; problems with processing and machining; problems with rust.	22
Mineral wool	Weak product; does not work well in cement.	22
Carbon fibers	Increases modular strength of cement sheet; is resistant to alkali attack; no increase in impact strength; very expensive.	22
Nylon	Provides impact strength; lacks reinforcement.	22
Ceramic fibers	No success to date; work is continuing.	22,31

A cost comparison of cement sheet products and siding products is presented in Tables 10 and 11, respectively.

TABLE 10. COMPARISON OF CEMENT SHEET PRODUCT PRICES²⁹⁻³⁴

Product	Cost (\$) per square meter (square foot)	
	1/4"	1/2"
J-M Flexboard® (A/C)	5.97 (0.55)	14.00 (1.30)
J-M Transite® (A/C)	13.15 (1.20)	21.50 (2.00)
Cement/wood board	1.95 (0.20)	4.00 (0.40)
High density GRC	—	8.61 (0.80)
Low density GRC	—	less than 0.60 (0.80)
Alumina-Sheet®	161.40 (15.00)	—

TABLE 11. COMPARISON OF SIDING PRODUCT COSTS²⁹

Product	Total cost (\$) per square meter (square foot)
Wood siding, 5/8"	8.60 (0.80)
Wood shingle	15.60 (1.45) ^a
Asbestos-cement shingle	13.50 (1.25) ^a
Fiber board	10.80 (1.00) ^a
Brick or stone	61.75 (5.75) ^a
Stucco or concrete block	17.90 (1.65) ^a
Aluminum	13.40 (1.25) ^a

^aCost includes material price for plywood sheathing of \$2.72/square meter (\$0.253 square feet).

SECTION 8

GASKETS AND PACKINGS

Gaskets and packings, used to seal one fluid from another, are found in virtually every mechanical, chemical, and thermal operation or device where fluids are involved. Asbestos has been successful in both applications because it is heat resistant, resilient, strong and relatively chemically inert.

Two types of substitute products exist for asbestos gaskets and packings: (1) fiber-for-fiber replacements; and (b) an alternative material, such as Glyon[®] or Nu-Board. The fiber-for-fiber replacements include: silica, carbon, Kevlar[®], ceramic and Teflon[®] fibers. Their characteristics are shown in Table 12.

TABLE 12. CHARACTERISTICS OF FIBERS

Fiber	Maximum tensile strength		Continuous-duty temperature limits (°C)		Chemical deterioration	References
	(10 ⁶ kPa)	(10 ³ psi)	Lower	Higher		
Silica	3,450	500	-73	990	Some molten metals, hydrofluoric acid, fluorides, oxides, hydroxides.	35-38
Ceramic	1,720	250	—	1,400	Hydrofluoric acid, phosphoric acid, hot concentrated alkalies.	39-41
Graphite	2,070	3,000	-200	3,000	Strong oxidizing compounds, chromium (VI) and permanganate solutions.	41, 42
Kevlar [®]	2,758	400	-46	200	Strong acids including: hydrochloric, hydrofluoric, nitric, and sulfuric.	43
Teflon [®]	359	52	-268	290	Certain perfluorinated organic liquids at temperatures above 299°C (570°F)	44
Asbestos	3,450	500	-273	540	Some molten metals, hydrofluoric acid, fluorides, oxides, hydroxides.	25

No single substitute fiber material possesses all desired qualities to the same degree as asbestos. However, for any particular application, a substitute fiber can often be employed to achieve the necessary combination of properties. Table 13 lists the raw materials identified as substitutes for asbestos-containing gaskets and packings.

For a fiber-for-fiber replacement, the cost of packings and gaskets is proportional to the cost of fibers used because the manufacturing processes are identical. A cost comparison of various fibers is presented in Table 14.

A cost comparison of asbestos gaskets and substitute gasket materials is shown in Table 15.

TABLE 13. NONASBESTOS RAW MATERIALS FOR GASKETS AND PACKINGS 45

Accopac	Fiberglass, silicone-coated	Paper
Acetate	Fiberglass, teflon-coated	Paper-base bakelite
Aluminum	Fibre-kork	Paper-base phenolic
Aluminum foil	Filter felt	Panelite
Armflex	Firm pad felt	Parchment paper
Artum shlm	Fishpaper (armite)	Phenolics
Asphalt-saturated sheathing felt	Flexible fibre	Plastics
Backcheck felt	Fluorglass	Polyamid
Bakelite	Fluorosilicone	Polyethylene, linear
Binders board	Foam	Polypropylene
Black fibre	Gasket felt	Pressboard
Blotting paper	Graphite-coated materials	Pure gum rubber
Bond paper	Graphited rubber	Red rope paper
Bunar	Gum rubber	Royal grey paper
Burite	Gummed kraft paper	Rubber-synthetic compounds
Buna N-rubber	Hemp	SBR rubber
Buna S-rubber	Hycar (GR-N) rubber	Saran screen
Cambric	Jute	Sheathing felt
Canvas	Jute-lined chipboard	Shim stock
Canvas-based bakelite	Jute paper	Showcase felt
Canvas-based phenolic	K-grey paper	Silicone
Cardboard	Kapton	Soft pad felt
Celluloid	Klingerit	Spauldite
Cellulose materials	Kraft paper	Spauldo
Cerafelt	Koroseal	Sponge rubber
Cerakote	Leather	Stencil board
Celcon	Leatherboard	Supercork
Chipboard	Lexide	Superpak
Chipboard-treated	Lexan	Teflon
Clear cellulose acetate	Linen-base bakelite	Teflon-coated fibreglass
Cloth	Linen-base phenolic	Thio-flex
Cloth-impregnated rubber	Manila paper	Thiokol-coated materials
Copper	Melamine	Thiokol-impregnated leather
Cork	Metal finishing felt	Transformer board
Cork-rubber compositions	Mold-resistant sheathing felt	Treated leather
Cork-synthetic compositions	Molybdenum filled materials	Trimming felt
Crepe barrier paper	Monocast nylon	Upholstery felt
Endening felt	Mylar	Urethane, homogeneous
Helrin	Mystik tape	Urethane, foam polyester
Huck	Natural rubber	Urethane, foam polyether
Duracel	Neoprene-asbestos, compressed	Urethane, foam scott felt
Durocork	Neoprene-coated materials	Urethane, liquid cast
Duroid	Neoprene-cork compositions	Urethane, millable gum
EPDM	Neoprene (GR-N) rubber	Varnished cambric
EPT	Nomex	Velbestos
Embossed chipboard	Nylatron	Vellumoid
Emery cloth	Nylon	Vinyl
Ethafnom	O ring cord	Vinylite
Fabric supported rubber	Oil-resistant material	Viton
Fairprene materials	Onion-skin paper	Viton sponge
Felt	P.V.C.	Vulcanized fibre
Fibre, vulcanized	Packtite	Waterproofed chipboards
Fitchboard		Wax-impregnated materials
Fibreflex		
Fiberglass		
Fiberglass, neoprene coated		

TABLE 14. COST COMPARISON BETWEEN ASBESTOS
FIBERS AND SUBSTITUTES FOR USE
IN TEXTILES (IN 1976 DOLLARS)^{3, 46}

Fiber	Approximate cost per pound (\$)
Asbestos fiber	1.00
Glass fiber	0.75
Nomex [®] - fiber	5.00-5.50
- continuous filament	6.50-10.00
Kevlar [®]	5.50-6.00
Teflon [®]	7.00-10.00
Kynol [®]	3.60
Carbon	2.00
Ceramics - 3M	30.00-32.00
- refrasil fibers	9.00
- refrasil strands	28.00

TABLE 15. COSTS OF ASBESTOS AND ASBESTOS
SUBSTITUTE GASKETING^{47, 48}

Material	Cost per square foot 1/16" diameter
Asbestos Sheet Garlock 900	1.95
Asbestos Sheet Garlock 7006	1.20
Gylon [®] Fawn	8.60
Vegetable Garlock 681	0.50
Cork	0.55
Red Rubber	0.40
Nu-Board 1800	0.90

SECTION 9

REINFORCED PLASTICS

Asbestos-reinforced plastic molding compounds are used in many industries, including the electrical, electronics, automotive, and printing industries. Asbestos fibers, when added to polymeric materials, modify the physical and chemical characteristics of the composite. The fibers serve as both fillers and reinforcing agents. Phenolic molding compounds (thermosetting polymers) are the major users of asbestos in reinforced plastic applications outside of floor coverings. In phenolic molding compounds, asbestos provides good surface finish, toughness, resistance to heat and fire, and less shrinking and warping than other fibers. Asbestos also improves the handling qualities of the product during processing.

Not all products require all of the physical properties supplied by asbestos, consequently substitutes that lack some physical properties of asbestos but meet product specifications can be used. In addition, new fiber technology has been developed which has improved physical properties of substitutes so that they are comparable to asbestos. Table 16 lists the substitute materials, their price compared to asbestos, and performance information and comments. Examination of the table shows a trend towards the replacement of asbestos in reinforced plastics.

TABLE 16. COST COMPARISON OF ASBESTOS AND SUBSTITUTE PRODUCTS
FOR REINFORCED PLASTICS²²

Substitute material	Price compared to asbestos	Performance and comments
Fibrous glass	75¢/lb vs 55¢/lb long fiber asbestos; 50¢/lb vs 10¢/lb short fiber asbestos	May be used for higher temperature applications; new glass fiber technology improves the physical properties of the material; problems with abrasiveness of glass wearing out processing equipment; process change probable.
Clay	Same	Used as filler, no reinforcement; new clay base compositions are reported to maintain the acceptable balance between heat resistance and impact strength.
Talc	8¢/lb vs 5-10¢/lb asbestos	Loss of strength but can compensate by making thicker walled product; presently used as an asbestos substitute; limited to 450°F applications.
Mica	5¢/lb vs 12-25¢/lb for asbestos	Adds dimensional stability and increases strength of plastics; mica's high aspect-ratio is purported to provide cost performance somewhere in-between that of inorganic particulate fillers and fiber reinforcement; it is blended with higher priced substitute materials.
Carbon fibers	\$10-\$12/lb vs 13-25¢/lb asbestos	For high strength applications; increases acid resistance in phenolics; also used as filler for thermoset plastics; high heat resistance; specialty applications only.
Aramid fibers	\$6-\$8/lb vs 13¢-25¢/lb for asbestos	Use in specialty plastic reinforcements; too expensive for asbestos replacement in phenolic molding compounds; can be blended with less expensive materials.
Polyethylene fibers	No data	Still in development stage; high modulus of elasticity (10 ⁶ psi) but poor heat resistance properties.
Calcium sulfate	2¢-3¢/lb vs 13¢-25¢/lb for asbestos	Provides improved output rates, allows high loadings, and results in low densities; high heat resistance; no reinforcing properties.

SECTION 10

TEXTILES

Asbestos textiles are used in the six product categories that follow.

FIRE-RESISTANT MATERIALS

Asbestos is used to manufacture fire-resistant materials because it is fireproof, acid-resistant and strong enough to be processed into textiles using looms and other equipment commonly employed in the textile industry. For example, asbestos cloth, yarn and thread are used to produce welding curtains, draperies, blankets, protective clothing, hot conveyer belts, furnace shields and molten metal splash protection aprons.

THERMAL INSULATION

Asbestos is used in thermal insulation because of its temperature resistance, high tensile strength, abrasion resistance, corrosion resistance and durability. Asbestos tubing, tape, rope, cord, cloth and yarn are used for safety protection in pipe wraps, stress relieving pads in welding operations, protective coverings for hot glassware utensils, coverings for diesel engine exhaust lines, flue sleeves, and braided walls in steam hose construction.

ELECTRICAL INSULATION

Asbestos yarn, roving, tape, thread, felts, cord, lap, and tubing are used for the insulation of wires and cables, arcing barriers in switches, circuit breakers, heater cords, and motor winding.

Asbestos textiles are employed in electrical insulation because of their high dielectric strength, temperature resistance, flexibility, abrasion resistance and high tensile strength.

PACKINGS AND GASKETS

Asbestos is also used in packings and gaskets in the textile industry. It provides these products with low thermal conductivity, resilience, chemical stability, immunity to thermal shock, compressibility, and abrasion resistance. For example, asbestos yarn, rope, wick, cord, cloth, and tape are used for pump packings, all purpose shaft and valve stem packings, expansion joints, manhole gaskets, seals for boilers, ovens and furnaces, flange gaskets and gaskets for storage tanks, coolers and dryers.

FRICTION MATERIALS

Asbestos textiles, usually in the form of woven yarn, are used in friction materials for brake linings, clutch facings, and brake pads, primarily because of their friction and wear characteristics.

SPECIALTY TEXTILES

Asbestos carded fiber is the main form of asbestos textiles that can be used in specialty products, such as liquid filters, electrolytic diaphragms, wiping pads and stuffing box packing. Asbestos carded fiber is well suited for these uses because of its filter medium qualities, chemical resistance and natural positive charge.

SUBSTITUTE MATERIALS

There is a large variety of fiber materials which can substitute for asbestos fibers. The physical properties of these substitutes for asbestos fibers in textile applications are presented in Table 17. Cost comparisons between asbestos fibers and substitute materials are presented in Table 18.

TABLE 17. PROPERTIES OF SUBSTITUTE FIBERS FOR ASBESTOS TEXTILE APPLICATIONS

Substitute material (manufacturer)	Product application	Properties		Comments	References
		Temperature resistance ^a up to °C (°F)	Tensile strength ^b kPa (psi)		
ASBESTOS:	All applications requiring an incombustible high temperature fabric.	649 ^c (1200) ^c	5.68×10^4 (824,000)	Low thermal conductivity; excellent radiation stability; good flexibility; excellent resistance to moisture and corrosion; excellent spinnability; contains a minimum of magnetic or conductive fibers.	39
GLASS:	All applications requiring an incombustible high temperature fabric.	538 (1000)	2.17×10^4 (315,000)	Density similar to asbestos; excellent handling characteristics; high dielectric strength; not as durable as asbestos; may produce some skin irritation; fiber diameter 0.066 mm (0.0026 inch).	3, 39
Refrasil [®] (Witco Materials)	Fire-resistant materials; thermal and electrical insulation; packings and gaskets.	982 (1800)	5.17×10^3 (75,000)	Good acid resistance; good dielectric properties; excellent resistant to thermal shock; high capacity to absorb moisture; lacks abrasion resistance, fiber diameter 8-12 microns.	50, 51
Thermo-Sil TM (Carlock, Inc.)	Fire-resistant materials; thermal and electrical insulation; packing and gaskets.	538 (1000)	2.17×10^4 (315,000)	Resists organic solvents and most acids and alkalis; resists abrasion and wear; moisture and weather resistant; dimensionally stable; high dielectric strength; low dielectric constant; soft and flexible.	52, 53
Zetex TM (Nevtex Industries, Inc.)	Fire-resistant materials; thermal and electrical insulation; packings and gaskets.	1538 (2800)	3.44×10^3 (500,000)	Excellent strength and durability; excellent dielectric strength; dimensional stability; excellent cutting, sewing and handling; abrasion resistant; fiber size 79 microns.	54, 55
CERAMICS:	All applications requiring an incombustible high temperature fabric.	1427 (2600)	high	A high tensile strength silica - alumina fiber; flexible; abrasion-resistant.	3
Nuxtel [®] 312 (JM Company)	Fire-resistant materials; thermal and electrical insulation; packings and gaskets.	1427 (2600)	1.72×10^3 (250,000)	High strength retention; low shrinkage; abrasion-resistant (after 4 hours at 816°C (1500°F), it retained 100% of its strength); good flexibility; some skin irritation; fiber size 10-12 microns in diameter.	56, 57
Thermo-Ceram TM (Carlock, Inc.)	Fire-resistant materials; thermal and electrical insulation; packings and gaskets.	1260 (2300)	1.72×10^4 (250,000)	Excellent resistance to mechanical vibration and stress; resists attack from most chemicals; no loss of strength due to water evaporation at high temperatures; low thermal conductivity and excellent electrical resistance.	52, 67
Fiberfrax [®] (Carborundum Co.)	Fire-resistant materials; thermal and electrical insulation; packings and gaskets.	1260 (2300)	1.72×10^4 (250,000)	Chemical resistant; low thermal conductivity; resists oxidation and reduction; excellent resistance to thermal shock.	68, 69

TABLE 17 (continued).

Substitute material (Manufacturer)	Product Application	Properties			References
		Temperature resistance ^a up to °C (°F)	Tensile strength ^b kPa (psi)	Comments	
PHENOLICS:					
Nomex [®] (DuPont Co.)	Fire-resistant materials; thermal and electrical insulation; packings and gaskets.	171 (700)	6.89 × 10 ⁷ (100,000)	Abrasion resistant; flexible; radiation resistant; chemical resistant; washable; low shrinkage.	3, 38, 39
Kevlar [®] (DuPont Co.)	Fire-resistant materials; friction materials; cables.	204 (400)	2.76 × 10 ⁸ (400,000)	High thermal stability; excellent chemical resistance; excellent cut resistance; low thermal conductivity.	3, 38, 60
Teflon [®] (DuPont Co.)	Fire-resistant materials; thermal and electrical insulation; packings and gaskets.	316 (600)	3.62 × 10 ⁵ (52,500)	High chemical resistance; low friction and adhesion; low shrinkage; great flex-abrasion resistance; radiation resistant.	3, 38, 61
Kynol TM (American Kynol, Inc.)	Fire-resistant materials; packings and gaskets.	704 ^d (1300) ^d	1.86 × 10 ⁵ (27,000)	Low moisture absorption; acid resistant; low toxic off gases; low shrinkage; is a carbon precursor; low abrasion.	62, 63
Durette [®] (Fire Safe Products, Inc.)	Fire-resistant materials.	593 (1100)	4.83 × 10 ⁵ (70,000)	Better heat stability than Nomex [®] ; high abrasion resistance; good acid resistance; high tear resistance; excellent dimensional stability.	3, 64
P.B.T. TM (Celanese Plastics and Specialties Co.)	Fire-resistant materials.	500 (932)	2.07 × 10 ⁴ (300,000)	Polybenzimidazole; nonflammable in air; little or no emittance of toxic off gases; acid resistant; readily processed on conventional textile equipment; comfortable; good cryogenic characteristics; high moisture repelling.	65, 66
Norfab [®] (AMATEX Corp.)	Fire-resistant material; thermal and electrical insulation; packings and gaskets.	343 (650)	Moderate	In a combination of synthetics; excellent workability; lightweight; high abrasion resistance; flexible; good chemical resistance.	76, 77
CARBON:					
	Fire-resistant materials; packings and gaskets; friction materials.	1427 (2600)	Over 3.10 × 10 ⁶ (450,000)	High flexibility, lightweight, good retention of fiber properties at high temperatures.	3, 70, 71
Carbon [®] (Celanese Plastics and Specialties Co.)	Friction materials; packings and gaskets.	5432 (1000) (no oxygen)	3.24 × 10 ⁸ (470,000)	Flexible, low shrinkage; excellent oxidative stability; excellent adhesion to organics; excellent electrical/thermal conductivity.	70, 71

TABLE 17 (continued)

Substitute material (manufacturer)	Product application	Properties				References
		Temperature resistance ^a up to °C (°F)	Tensile strength ^b kPa (psi)	Comments		
Cellon TM (Celanese Plastics and Specialties Co.)	Fire-resistant materials.	760 (1400)	2.10×10^5 (30,300)	Lightweight, flexible, high moisture regain, low density, readily converted into carbon.		70, 72
QUARTZ:						
Alphaquartz ^B (Alpha Associates)	Fire-resistant materials; thermal and electrical insulation; packings and gaskets.	Over 1204 (2200)	8.69×10^7 (126,000)	Thermal stability; elastic; excellent resistance to thermal shock; easily impregnated; excellent abrasive characteristics; high purity; transparent to electromagnetic and radio waves.		73, 74, 75
NATURAL FIBER:						
Cotton (Vestex, Inc.)	Fire-resistant materials	232 (450)	8.62×10^5 (125,000)	Flame resistant; is coated and treated; washable; fiber diameter 0.020 to 0.030 mm (0.0008 to 0.0011 inches).		49, 78

^aTemperatures depend upon product application.^bFigures are for fibers only, and are not necessarily related to fabric strength.^cWire inserted asbestos textiles.^dCarbonizing temperature range.

TABLE 18. COST COMPARISON BETWEEN ASBESTOS
FIBERS AND SUBSTITUTES USED IN
TEXTILES^a

Product	Approximate cost (\$) per kilogram (pound)	Reference
Asbestos	0.45-0.50 (1.00-1.10)	3
Fiberglass	0.50 (1.10)	3
Kevlar®	2.50-2.70 (5.50-6.00)	58
Nomex®	2.70-2.95 (6.00-6.50)	58
Teflon®	3.15-4.50 (7.00-10.00)	58
Refrasil®	3.15-5.40 (7.00-12.00)	50
Durette®	3.60 (8.00)	64
Nextel® 312	13.50 (30.00)	56
Kynol™	2.00-2.25 (4.50-5.00)	62
Celiox™	4.50 (10.00)	70
Celion®	11.25 (25.00)	70

^aPrices vary with product style and quantity.

SECTION 11
MISCELLANEOUS

DRILLING MUDS

Drilling muds or drilling fluids are used when wells are drilled by the rotary method. Asbestos increases the carrying capacity of the mud (the ability of the mud to bring up cuttings) without significantly increasing the mud viscosity and acts as a loss-circulation material in helping to plug passages in the drill hole. No single substitute except possibly bentonite or attapulgite clays serves both of these functions, but several substitutes can be used as viscosifiers and many additional materials can be used as loss-circulation materials.

A list of both commonly substituted drilling mud viscosifiers and loss-circulation materials as well as a cost comparison with asbestos is in Tables 19 and 20.

TABLE 19. COST COMPARISON OF DRILLING MUD VISCOSIFIERS

Material	Cost (\$/pound)	Amount used/ barrel (pounds)	Cost (\$/barrel)	Reference
Asbestos	0.40 - 1.00	2 - 5	0.80 - 5.00	79, 80
Bentonite	0.05 - 0.10	20 - 40	1.60 - 4.00	79
Attapulgite	0.15 - 0.20	15 - 20	2.40 - 4.00	79
Sepiolite	0.20 - 0.25	5 - 10	1.00 - 2.50	79
Xanthan (XC) polymer	7.00 - 9.00	0.5 - 2	3.50 - 18.00	79
Carboxymethyl cellulose	3.60	0.25 - 2	0.90 - 7.20	80
Polysaccharides polymer (DF-VIS)	5.00	1 - 2	5.00 - 10.00	81
Hydroxyethyl cellulose	1.00	8 - 9	8.00 - 9.00	82

TABLE 20. COSTS OF COMMON LOSS-⁸¹
CIRCULATION MATERIALS

Material	Cost (\$/pound)
Asbestos	0.45
Cellophane flakes	0.40
Mica	0.35
Nutshells	0.30
Bentonite	0.10

OTHER PRODUCTS

Other minor uses of asbestos fibers include:

- Shotgun shell base wads
- Asphalt/asbestos cement
- Foundry sands
- Sprayed on insulation
- Artificial fireplace ashes and artificial snows.

The present use of asbestos in shotgun shell base wads appears to be negligible; one-piece polyethylene shells may serve as alternatives. While there is some indication that asbestos may improve the quality of asphalt cement, the prevailing opinion appears to be that if there is actually anything to be gained by adding asbestos, it is not enough to make it worthwhile.⁸³ In foundry sands, asbestos is actually an undesirable material because it lowers the refractory point of the sand mold.⁸⁴ Substitutes used in insulating sleeves on risers for foundry sand castings can be any inert mineral material that (a) withstands high heat, (b) insulates, and (c) will not crystallize with water at high temperatures.*

The use of asbestos in sprayed-on insulation was regulated in 1973,^Δ effectively eliminating further use of asbestos in this product. Substitute materials include both cellulose fibers and rock wool, both of which are made to be fire retardant, cost-effective, and, at present, have demonstrated no adverse health effects. Artificial fireplace ashes containing asbestos were banned in 1977⁸⁵; vermiculite, rock wool, mica, and synthetic fibers have since replaced asbestos in this use. Health considerations have also nearly halted the use of asbestos in artificial snows.

* To date, materials developed are proprietary.

Δ National Emissions Standard for Asbestos (40 CFR 61).

TABLE 21. SUBSTITUTE PRODUCT CHARACTERISTICS

Asbestos product category	Availability	Performance characteristics	Costs	Comments
1. Paper Products				
a. Beverage filters	Commercially available	Meets most requirements	Higher	For ease removal, asbestos still superior.
b. Millboard	Commercially available	Meets some requirements	Higher	Substitutes not available for all applications.
c. Commercial papers	Commercially available	Meets some requirements	Much higher	Substitutes not available for all applications.
d. Paper-laminated	Commercially available	Meets all requirements	Comparable	Durability may not equal asbestos.
e. Roofing felt	Commercially available	Meets all requirements	Comparable	Some substitutes preclude asbestos; heat covering varies with roof.
f. Heater-add asbestos	Limited availability	Not sufficient	Higher	Substitutes only available for limited application.
g. Electrical insulation	Commercially available	Meets all requirements	Higher	Extensive substitute products available.
h. Floor tile felt	Under development			Material substitutes such as carpet readily available. Fiber felt substitute still under development.
i. Pipeline wrap	Commercially available	May be less durable	Higher	Asbestos pipeline wrap presently preferred.
2. A/C Pipe				
	Commercially available	Meets all requirements	Comparable	Several available substitutes.
3. Floor Tiles				
	Commercially available	Less durable	Higher	Currently, no substitutes comparable to asbestos.
4. Friction Products				
a. Automobile brakes	Commercially available	Meets all requirements	Comparable	Proprietary composition.
b. Non-safety truck brakes	Commercially available			—
c. Ball joint brakes	Commercially available			—
d. Aircraft brakes	Commercially available	Meets all requirements	Higher	All new brakes correct; some asbestos still in use.
e. Industrial brakes	Under development			Some diverse uses.
f. Vehicle clutches	Under development			
g. Industrial clutches	Under development			
5. Sealants				
a. Asbestos-based	Under development	Expected to be less durable	Comparable	Specialty treated cellulosic fibers.
b. Non-asphalt based	Commercially available	Meets some requirements	Generally higher	Asbestos banned in some products.
6. A/C Sheet				
	Commercially available	Meets most requirements	Some higher	Substitutes for high temperature applications more costly.
7. Gaskets and Packings				
	Commercially available	Meets most requirements	Variable	Equipment redesign required in certain cases.
8. Reinforced Plastics				
	Commercially available	Meets most requirements	Variable	Some manufacturers have already switched to substitutes.
9. Textiles				
	Commercially available	Meets most requirements	Higher	Substitutes available for most applications.
10. Miscellaneous				
	Commercially available	Meets most requirements	Some higher	Some asbestos products banned; drilling mud substitutes may be much more expensive.

SECTION 13
REFERENCES

1. Fiero, J. V., and R. A. Sabineau. Filtration - An Old Process With a New Look. Food Technology, 33(4):67-72, 1979.
2. Gordon, W. A., and V. E. Riddle. Industry Profile and Background Information on Asbestos Cement Products, Millboard and Lumber-Related Products. U.S. Consumer Product Safety Commission CPSC-C-7A-0091, Task 2, Subtask 2.02, February 1979.
3. A. D. Little Inc., and Sorel, Inc. Characterization of the U.S. Asbestos Papers Markets. Prepared for the Minister of Industry and Commerce - Government of Quebec; Final Draft Report to Sorel Inc. (Montreal), Report C-79231, 1978.
4. Chlorine Institute Comments to ANPRM, p.4, 1980.
5. Telecon. Sales Personnel, Garbrundum Corporation, Niagara Falls, N.Y., with D. Ramsay, GCA/Technology Division, August 1979.
6. Telecon. Stein, C., Sales Representative, Para Manufacturing Co., Ambler, PA. [(213) 646-1300], with D. Ramsay, June 24, 1979.
7. Telecon. Kiser, W. F., Marketing Manager, Ceraform Products, John-Manville Corp., Manville, N.J. [(201) 725-5000], with D. Ramsay, GCA/Technology Division, August 12, 1979.
8. EPA Preliminary Estimates.
9. Telecon. McLaughlin, G., Estimator, C and M Roofing, Somerville, Massachusetts, [(617) 623-1042], with D. Ramsay, GCA/Technology Division, August 20, 1979.
10. Telecon. Estimator, Hatich Roofing Company, Chelsea, Massachusetts, [(617) 322-3100], with D. Ramsay, GCA/Technology Division, August 20, 1979.
11. Telecon. Noble, A., Assistant Sales Manager, Koppers Company, Eastern Division, West Orange, N.J., [(201) 734-9150] with D. Ramsay, GCA/Technology Division, August 30, 1979.
12. Telecon. Perkins, G., R-625 Products Marketing Manager, Owens-Corning Company, Toledo, Ohio [(419) 244-7841], with D. Ramsay, GCA/Technology Division, August 29, 1979.
13. Telecon. Salesman, Bradco Supply Corporation, Woburn, Massachusetts, with D. Ramsay, GCA/Technology Division, August 17, 1979.
14. Telecon. Pipeline wrap user with N. Pillsbury, EPA OPTS, June 1980.
15. Survey of Water Main Pipe in U.S. Utilities Over 2,500 Population. American City. Morgan-Graham Pub. Co. Pittsfield, Mass. 1975.
16. Transite Class Pressure Pipe on Transite Sewer Pipe. Pricing schedule. John-Manville, Denver, Colorado. January 1980.
17. Telecon. Owen, Gene. American Cast Iron Pipe Company, [(201) 845-5440] with E. Musler, GCA/Technology Division. February 26, 1980. Notebook 3. Call 22.
18. Telecon. McKenna, Robert. Portland Stoneware, [(617) 864-7523], with E. Musler, GCA/Technology Division. February 26, 1980. Notebook 3. Call 23.
19. Telecon. Andrews, Charles. New England Concrete Pipe, [(617) 969-0220], with E. Musler, GCA/Technology Division. February 26, 1980. Notebook 3. Call 25.
20. Telecon. Hoffmann, Richard. Scituate Concrete Pipe Company, [(617) 545-0564], with E. Musler, GCA/Technology Division. February 28, 1980. Notebook 3. Call 25.
21. Telecon. Chabon, Roger. Portland Plastic Pipe, [(207) 774-0364], with E. Musler, GCA/Technology Division. February 28, 1980. Notebook 3. Call 26.
22. Wright, M.D., et al. Asbestos Dust Feasibility Assessment and Economic Impact Analysis of the Proposed Federal Occupation Standard, Part 1: Technological Feasibility Assessment and Economic Impact Analysis. U.S. Department of Labor. Occupational Safety and Health Administration. Washington, D.C. Contract No. J-9-7-9-0224. Task 2. September 1978.
23. Telecon. Jackn, M., Bendix Research Labs with N. Roy, GCA/Technology Division. August 1979.
24. Telecon. Jackn, M., Bendix Research Labs with N. Roy, GCA/Technology Division. November 19, 1979.
25. Meylan, W.M., et al. Chemical Market Input/Output Analysis of Selected Chemical Substances to Assess Sources of Environmental Contamination: Task III - Asbestos. EPA-360/6-78-005. August 1978. pp. 63-65.

26. Telecon. Brzezowski, Ken, TREMCO, Inc. with D. Cook, GCA/Technology Division. January 18, 1980. Substitute fibers for roofing products.
27. Telecon. Norman, Chla, Koppers with D. Cook, GCA/Technology Division. February 6, 1980. Roofing materials.
28. Telecon. Jones, J., Assistant General Manager, Cam-FIL Corp., Nashville, Tennessee, [(615) 883-7363], with S. Dulatsky, GCA/Technology Division, January 31, 1980. Notebook No. 03, Phone call No. 23.
29. International Housing Corporation. Notebook containing information about Cement/Veneer Board. Sacramento. California. 1979.
30. Telecon. Lewis, W.R., CRC Products, Inc., Schertz, Texas, [(512) 651-6773], with S. Dulatsky, GCA/Technology Division, February 11, 1980. Notebook No. 03, Phone call No. 30.
31. Telecon. Chaille, C., Babcock & Wilcox Refractories Division, Augusta, Georgia, [(404) 798-8000] with S. Dulatsky, GCA/Technology Division, January 30, 1980. Notebook No. 03, Phone call No. 30.
32. Telecon. Reeling, C., Zircar Products, Inc., Florida, New York, [(914) 651-4481] with S. Dulatsky, GCA/Technology Division, February 5, 1980. Notebook No. 03, Phone call No. 38.
33. Cape Boards and Panels, Ltd. Honolulu Industrial Handbook. M1077914. Unbridge, England.
34. Telecon. Boston, J., Asbestos Fabricators, Inc., Charlotte, North Carolina, [(704) 377-3400], with S. Dulatsky, GCA/Technology Division, March 7, 1980. Notebook No. 03, Phone call No. 90.
35. Araco, Nitco Materials Division Refrasil Insulation Textiles Can Take This Test! Can You? LNT/MD-10079 10 M CP 11-79. Gardena, California. November 1979.
36. Colt Industries, Carlock Inc. Mechanical Packing Division, Industrial Packing. Thermo-Resil - Textured Fiberglass Cloth, Tape, Tubing. A Non-Asbestos Product. LX-7/79-iC M. Palmyra, New York, July 1979. 7 pages.
37. Kewtex Industries Inc. Baton - All of the Protection But None of the Health Hazards of Asbestos. Victor, New York. 4 pages.
38. Araco. Nitco Materials Division, Refrasil - Refractory Silica in Textile Form Insulation Product Data Bulletin All Products. P.O. LNT/MD-1779 13 M CP 11-79. Gardena, California. November 1979. 4 pages.
39. Ceramic Fiber Products/JM. Notes - 312 Ceramic Fiber from JM. N-MNPOL (79.5) MF St. Paul, Minnesota. 4 pages.
40. Colt Industries, Carlock Inc. Mechanical Packing Division. Compression Packing. Thermo-Ceram. CNP-121. Sodas, New York. February, 1979. 2 pages.
41. Colt Industries, Carlock Inc. Mechanical Packing Division. Non-Asbestos Packings, Gaskets, Dynamic Seals, Expansion Joints, Oil Seals, Fiberglass Cloth. MP-902. Palmyra, New York. August 1979. 9 pages.
42. Araco. Nitco Materials Division. Nitco Aerospace Materials. LNT/MD-3278 3M TC 9-78. Gardena, California. September 1978. 3 pages.
43. E.I. DuPont de Nemours & Co. Inc. Textile Fibers Department. Characteristics and Uses of Kevlar 29 Aramid Number 375. Wilmington, Delaware. September 28, 1976. 7 pages.
44. E.I. DuPont de Nemours & Co. Inc. Properties, Processing and Applications of Teflon TFE Fluorocarbon Fiber. Bulletin TF-2, Wilmington, Delaware. May 1978. 15 pages.
45. Incoflex, Inc. Advertising List of New Materials, Publication Number 49738. Rockford, Illinois. 1 page.
46. Telecon. Chiontergi, R., Marketing Manager, E.I. DuPont de Nemours & Co. Inc., Wilmington, Delaware, [(302) 993-3931] with T. Henderson, GCA/Technology Division, February 1, 1980. Notebook No. 07, Phone call No. 20.
47. Swanson, R.C., Sales Representative, Colt Industries, Carlock Inc. Mechanical Packing Division, Charlotte, N.C. Meeting with T. Curtin, GCA Corporation February 21, 1980.
48. Telecon. Connolly, T., Jones Industrial Insulation Corp., Moonachie, New Jersey, [(201) 933-3834], with T. Curtin, GCA/Technology Division, February 27, 1980. Notebook No. 06, Phone call No. 42.
49. Anon. Handbook of Asbestos Textiles. American Textile Institute. 1967.

30. Telecon. Black, W., Sales Representative, Nitro Materials Division, Cardena, CA. [(213) 321-8000], with T. Henderson, CCA/Technology Division, January 30, 1980, Notebook No. 07, Phone call No. 11.
31. Nitro Materials Division Softcell Product Data Bulletin. P.O. LRT/MD-1779 13 M CP and LRT/MD-273 6M CP. Cardena, CA. November 1979. p. 1-2.
32. Telecon. Angelino, J., Textiles Marketing Manager, Corlock Inc., Palmyra, NY, [(315) 397-4811] with T. Henderson, CCA/Technology Division, February 8, 1980, Notebook No. 07, Phone call No. 31.
33. Corlock Inc. Thermo-BilTM, A Non-Asbestos Fabric. LX-7/79-10M. Palmyra, NY. July, 1979. p. 1-6.
34. Telecon. Dinit, B., President, Newton Industries, Inc., Victor, NY, [(716) 924-9133] with T. Henderson, CCA/Technology Division, January 30, 1980, Notebook No. 07, Phone call No. 11.
35. Newton Industries Inc. ZetexTM Bulletin. Victor, NY. 1979.
36. Telecon. Ellingson, L., Sales Representative, Ceramic Fiber Products/JM Company, St. Paul, MN, [(612) 733-1330], with T. Henderson, CCA/Technology Division, January 31, 1980, Notebook No. 07, Phone call No. 18.
37. Ceramic Fiber Products, JM Company. Nextel 312 Ceramic Fiber Products. N-MTDS (79.3) MP. and N-MPDSB-(89.5) 11. St. Paul, MN.
38. Telecon. Chiostrugi, R., Marketing Manager, E.I. DuPont de Nemours & Co., Inc. Wilmington, DE. [(302) 999-3931], with T. Henderson, CCA/Technology Division, February 1, 1980, Notebook No. 07, Phone call No. 20.
39. E.I. DuPont de Nemours & Co., Inc. DuPont Technical Information Bulletin. N-236. Wilmington, DE. October 1969. p. 1-12.
40. E.I. DuPont de Nemours & Co., Inc. Characteristics and Uses of Kevlar 29 Aramid. N-373. Wilmington, DE. September 1976. p. 1-7.
41. E.I. DuPont de Nemours & Co., Inc. Properties, Processing and Applications of Teflon. TR-2. Wilmington, DE. May 1978. p. 1-15.
42. Telecon. Storti, M., Marketing Manager, American Kynol Inc., New York, NY, [(212) 278-2838], with T. Henderson, CCA/Technology Division, February 1, 1980, Notebook No. 07, Phone call No. 23.
43. American Kynol, Inc. KynolTM Novoloid Bulletin. A-10, DDJ. New York, NY. October 1974. p. 1-11.
44. Telecon. Vance, R., Vice President, Fire Safe Products Inc., St. Louis, MO, [(314) 423-6989], with T. Henderson, CCA/Technology Division, February 20, 1980, Notebook No. 07, Phone call No. 35.
45. Celanese Corp. PSITM, Polybenzimidazole Fiber. Charlotte, NC, February 1979. p. 2.
46. Telecon. McCallister, K.C., Marketing Manager, Celanese Corporation, Charlotte, NC, [(704) 354-2000], with T. Henderson, CCA/Technology Division, February 1, 1980, Notebook No. 07, Phone call No. 22.
47. Corlock Inc. Thermo-CeranTM. LX-7/79-11 M. Palmyra, NY. p. 1-6.
48. Telecon. Piatek, E., Textile Specialist, The Carborundum Company, Niagara Falls, NY, [(716) 278-2000], with T. Henderson, CCA/Technology Division. January 30, 1980, Notebook No. 07, Phone call No. 08.
49. The Carborundum Company. Fiberfrax Product Bulletin. C736-A-C. Niagara Falls, NY. p. 1-10.
50. Telecon. Timmons, B., Marketing Supervisor, Celanese Plastics and Specialties, Chatham, NJ, [(201) 635-2600], with T. Henderson, CCA/Technology Division, January 28, 1980, Notebook No. 07, Phone call No. 03.
51. Celanese Plastics and Specialties Co. Celion Carbon Filters Bulletin. Chatham, NJ. November 1979.
52. Celanese Plastics and Specialties Co. CelionTM Fibers Bulletin. Chatham, NJ. November 1979.
53. Telecon. Saffadi, R., President, Alpha Associates, Woodbridge, NJ, [(201) 634-3700], with T. Henderson, CCA/Technology Division, January 31, 1980, Notebook No. 07, Phone call No. 11.
54. Alpha Associates Inc. Alpha quartz Bulletin. Data sheets Nos. 11690-11693, Woodbridge, NJ. May 1979.
55. Lubin, G. High Silica and Quartz. In: Handbook of Fiberglass and Advanced Plastic Composites. Reinhold Book Corporation. 1969. p. 191-200.

76. AMATEX Corp. An Improved Alternative, Norfab Series 400. Harrisburg, PA. 1979.
77. Telecon. MacKnight, W., Sales Manager, AMATEX Corp., Harrisburg, PA, [(215) 277-6100], with T. Henderson, CCA/Technology Division, February 1, 1980, Notebook No. 07, Phone call No. 21.
78. Telecon. Wilander, R., Sales Manager, Mastex Inc., Chicago, Illinois, [(312) 523-8331], with T. Henderson, CCA/Technology Division, January 30, 1980, Notebook No. 07, Phone call No. 10.
79. Telecon. Petcherych, D., Sales Division, Merch Co., Houston, TX, [(713) 621-0110], with L. Pilcher, CCA/Technology Division, January 24, 1980, Notebook No. 04, Phone call No. 9.
80. Telecon. Clear, E.E., Drilling Specialist, Bartlesville, OK, [(918) 641-3403], with L. Pilcher, CCA/Technology Division, January 24, 1980, Notebook No. 04, Phone call No. 5.
81. International Drilling Fluids, "Price List, 1979," Middlesboro, England, February 26, 1979.
82. Telecon. Johnson, G., Brinadd Company, Houston, TX, [(713) 644-1895], with L. Pilcher, CCA/Technology Division, January 30, 1980, Notebook No. 04, Phone call No. 14.
83. Telecon. Foster, C., Consultant, National Asphalt Paving Association, Riverdale, MD., [(301) 779-4880], with S. Duletsky, CCA/Technology Division, February 11, 1980, Notebook No. 05, Phone call No. 19.
84. Telecon. Koteln, Eero, American Laundrymen's Society, Des Plaines, IL [(312) 824-0181], with L. Pilcher, CCA/Technology Division, February 13, 1980, Notebook No. 04, Phone call No. 39.
85. Part 1305 - Ban of Artificial Emberising Materials (Ash and Embers) Containing Respirable Free-Form Asbestos. Federal Register, Chapter 11 - Consumer Product Safety Commission, December 13, 1977.