

CG 20 CODE BC-2-A PKG.

EST. WGT.

2068

LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

(C) BC-2-A

APPROVED BY
AJC 11-16-77
DCG 1-13-78

TYPED BY
NSA 3-14-78

MAKING NOTES

REMARKS

NAME: MONASTRAL® BLUE B

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	5-5-87			STARTED	2 PM				
TIME	2:00 PM			CAKES USED	49				
RELEASED BY	SS			WATER ON	2 PM				
PRESS	31			HRS. WASHED	3 1/2				
NO. OF CAKES	44			OHMS	4600				
PRESS WITH	AGITATION			HRS. WASHED					
WASH TO 3000	OHMS 135-145°F water			OHMS					
TEST AFTER 20	HOURS			HRS. WASHED					
LOAD in metal drums at 360# net wgt.				OHMS					
NOTE:	1. Request making reheat SV to 178-182°F once per shift			CAKE CONDITION					
	2. Air-blow presscake when 3000 ohms reached for 15 min at 40 PSI			NO. CARS LOADED					
				EXPLAIN LOSSES					

SAMPLES Thief sample per SOP

DELIVER TO CTI

SAMPLED BY BFL

RELEASED BY

-DRYING-

DO NOT DRY

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS

SAMPLES

[illegible]

LUMP WGT.

DELIVER TO

SAMPLED BY

RELEASED BY

-GRINDING-

MILL	SCREEN	RPM
------	--------	-----

MAX. TEMP.

OF

SCREEN

MAX. TEMP.

RPM

Q-F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING

SAMPLES

DATE MIXED

DELIVER TO

CTL

SAMPLED BY

RELEASED BY