

Goods	SHADE WHITE BASE					TORONTO		1804
Consistency						Date	2-12-3	Old No.
For Use on						Classification No.		
Material	Code	1	5	Bbl.			Manufacturing Specification	
Raw Oil	01		48	gals			Grind	
HP AL OIL	063		6				Kind of Mill	
TEXACO	S43		1 1/2				Rate per hr.	
KINGSLEY	810		3 3/4				Wt. per gal.	Baume
WATER	SIC		3/4				Strainer	Viscosity
							Flash Point	
Carb. Lead	W2		135	"			Testing Requirements	
2% LEADED ZINC	W16		495	"			Reduce with	
Amaloid	W69		135	"			Amount	
Silica	W15		35	"			Apply by	
Peel	W11		100	"			Surface	
							Drying time	
							Baking time	
							Match for	
							Std. Yield	

N12050

