

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE

YT562

LOT

38699

NET WT/PKG

NO. PKG

PACK. WGT

LOCATION

PQ

23

2534

31

STUMP

Lamp

2548

TOTAL NET WT.

2534

PKG. N-CODE

PROD. SPVR

DATE

WHSE. OPER.

JLB

1/31/11

292

N 31792

0.0

108.+
119.+
117.+
113.+
110.+
118.+
127.+
112.+
114.+
112.+
100.+
90.+
116.+
107.+
107.+
120.+
135.+
127.+
125.+
125.+
128.+
94.+
30.+
2534.T

N 31792.01

DUP050292074

→ JAN 19 81 38699
EST. WGT. 2525 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
YT-562-D (P)	BBK 01-16-78
	AMJ 12-14-78

TYPED BY
emw121578

MAKING NOTES

REMARKS

NAME: GREEN GOLD

NON-BLEEDING

INSTRUCTIONS

- PRESSING -

RECORD

VAT	105					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	1-12-81					STARTED	5:30				
TIME	8:45					CAKES USED	60				
RELEASED BY						WATER ON	4pm				
PRESS	32	33	35	36		HRS. WASHED	9				
NO. OF CAKES	60	60	60	64		OHMS	4500				
PRESS	without	AGITATION				HRS. WASHED					
WASH TO	4000	OHMS with	135-145°F	water		OHMS					
TEST AFTER	9	HOURS				HRS. WASHED					
LOAD	on 7 cars					OHMS					
						CAKE CONDITION	6				
						NO. CARS LOADED	6				
						EXPLAIN LOSSES					

SAMPLES 8 OZ
DELIVER TO Hold for P E

SAMPLED BY	RELEASED BY
------------	-------------

-DRYING-

Dry 20 Hrs at 200°F

LUMP: - OK - WET - SALTS - CONTAMINATE

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 8 OZ
DELIVER TO Hold for P E

NO. CARS PULLED	LUMP WGT. 2548
SAMPLED BY	RELEASED BY BLL

-GRINDING-

MILL 8 HSP $\frac{1}{8}$ " RP SCREEN 3560 RPM
MAX. TEMP. 150 °F

SCREEN	RPM
MAX. TEMP.	°F

EXPLAIN LOSSES

DATE MIXED

SAMPLED BY

RELEASED BY

DUP050292075

N 31792.02

38699/
5100
18

0.00 *
2.05 +
0.12 -
2.18 +
0.12 -
2.00 +
0.12 -

2.21 +
0.12 -
2.18 +
0.12 -
2.20 +
0.12 -
2.16 +

0.12 -
2.11 +
0.12 -
2.25 +
0.12 -
2.13 +
0.12 -

2.16 +
0.14 -
2.02 +
0.14 -
1.45 +
0.14 -
25.48 *

N 31792.03

DUP050292076