

(DRY AND PASTE ONLY)

15737

37227

PO

1670

7

T-144

1600

1

 $\gamma = 1.31$

STUMP

4000 3.200

TOTAL NET WT

3270

PKG. N-CODE

PROD. SPVR

574

DATE _____

10-3-82

WHSE. OPER.

PROCESSING INSTRUCTIONS: BATCH UNIT

CG 03 CODE KY-787-D PKG.
 → SEP-25-80 37227
 EST. WGT. ~~1800~~ 932 LBS.

PROCESSES KY-787-D (Q)
 APPROVED BY EWK 9/22/76
 DCG 9/27/76
 RETYPED BY
 CJH 4/2/80

MAKING NOTES

REMARKS

TOTAL WGT 3332#

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT	244				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	9-26-80				STARTED	11 AM				
TIME	3:10 AM				CAKES USED	46				
RELEASED BY	(22) C.M.				WATER ON	3				
PRESS	22	23	24	25	HRS. WASHED	5000				
NO. OF CAKES	46	46	52	48	OHMS					
PRESS WITH					HRS. WASHED					
WASH TO 2000					OHMS					
TEST AFTER 2					HRS. WASHED					
LOAD ON 6 CARS					OHMS					
					CAKE CONDITION	6				
					NO. CARS LOADED	6				
					EXPLAIN LOSSES					

SAMPLES 1-8 OZ JAR
 DELIVER TO CTL FOR COLOR

SAMPLED BY

RELEASED BY IDS

-DRYING-

DRY 12 HRS AT 220 °F
 THEN DRY 6 HRS AT 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
 DELIVER TO

NO. CARS PULLED
 SAMPLED BY

NO. DRUMS 14
 LUMP WGT. 3289
 RELEASED BY Bhh

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
 MAX. TEMP. 150 °F

SCREEN RPM
 MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING
 SAMPLES 1 ENV & 1 PT. CAN
 DELIVER TO CTL

DATE MIXED

SAMPLED BY

RELEASED BY

37227
41
17

23 03 +
2 55 +
0 12 -
2 58 +
0 12 -
2 60 +
0 12 -
2 45 +
0 12 -
32 6 2
32 6 2

23 19
2 12