CODE 42-16-B LOT E1337

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
50	60	3,000		
STUMP	Lump	3,195		

TOTAL NET WT. 3 (00) PKG. N–CODE 1000

PROD. SPVR. DATE WHSE. OPER.

JO 5/15/81

92/245

CG 01 CODE YC-16-B PKG. 93

→ MAY -0-81-E-1337

EST. WGT. 3130 LBS.

Red FP

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
(A) YC-16-B	A.C 4-7-75
	JFH 5-5-75
	DCG 5-14-15
TYPED BY	

MAKING NOTES

REMARKS

NAME: MOLYBDATE ORANGE NON-BLEEDING

E C INSTRUCTIONS

VAT	245				
DATE	5-12				
TIME	4:00 PM				
RELEASED BY	ZJ				
PRESS	91	92	93	2	25
NO. OF CAKES	42	32	32	32	32

PRESS AGITATION

WASH TO 2000 OHMS

TEST AFTER 2 HOURS WITH 35-75 F WATER

LOAD ON 4 CARS

SAMPLES

DELIVER TO

-PRESSING- RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	945 AM				
CAKES USED	32				
WATER ON	3 PM				
HRS. WASHED	5				
OHMS	2500				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	4				

EXPLAIN LOSSES

SAMPLED BY RELEASED BY

-DRYING-

DRY 16 HOURS AT 220 F

LUMP: - OK - WET - SALTS - CONTAMINATED

DRYER SECTIONS USED:

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 13

SAMPLES

DELIVER TO

NO. CARS PULLED 4 LUMP WGT. 3125

SAMPLED BY RELEASED BY

-GRINDING-

MICROATOMIZE

SET ROOF GATE AT 5 INCHES AIR FLOW

MAGNEHELIC READING ON ATOMIZER PANEL 1.0"

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING

SAMPLES 1 ENV

DELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

DUP050096150

YC-16B

1337
41
158

0.00 *

3.43 +
0.12 -
3.19 +
0.12 -
0.77 +
0.12 -
7.03 *

158

0.00 *

7.03 +
3.04 +
0.12 -
3.05 +
0.12 -
3.12 +
0.12 -
2.92 +
0.12 -
2.95 +
0.12 -
2.94 +
0.12 -
[redacted] +
[redacted] -
24.26 *

24.26 +
2.87 +
0.12 -
2.43 +
0.12 -
2.75 +
0.12 -
38.95 *

DUP050096151