

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE AT698 LOT 38442
NET WT/PKG NO. PKG PACK. WGT LOCATION PO

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
<u>14</u>	<u>2119</u>	<u>21</u>		

STUMP

Lump 2104

TOTAL NET WT. 2119 PKG. N-CODE 2104

PROD. SPVR. DATE WHSE. OPER.

[Signature] 1/10/01 292

N35074

0.T

1:4.+
1:4.+
1:1.+
1:5.+
1:2.+
1:0.+
1:4.+
1:2.+
1:3.+
1:6.+
1:3.+
1:8.+
1:8.+
1:9.+
21:9.T

PROCESSES	APPROVED BY
RT-698-D (L)	JJG 1/24/78
	DCG 1/26/78

→ DEC 29 80 38442
EST. WGT. ~~2220~~ 3074 * LBS.

INSTRUCT MAKING AREA TO ADD 10#
N-588-A HALFWAY THRU PRESSING

TYPED BY

MAKING NOTES

REMARKS

NON-BLEEDING

RECORD

VAT		901				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE		1-5-81				STARTED	3:30				
TIME		300 A				CAKES USED	62				
RELEASED BY		JDC				WATER ON	1:30 PM				
PRESS	32	(37)				HRS. WASHED	8				
NO. OF CAKES	60	(62)				OHMS	4000				
PRESS with		AGITATION				HRS. WASHED					
WASH TO	3000	OHMS with 35-75°F water				OHMS					
TEST AFTER	6	HOURS				HRS. WASHED					
LOAD on 10 cars						OHMS					

Cleaned By _____ Time Cleaned _____

EXPLAIN LOSSES

**SAMPLES
DELIVER TO**

SAMPLED BY	
------------	--

RELEASED BY

-DRYING-

DRY	12 -	HOURS AT	- 220	°F
Then Dry 12 hrs at 200°F				
Hold on track for 30 min before dumping				

LUMP: - OK - WET - SALTS - CONTAMINATE

ADDITIONAL DRYING HOURS REQUIRED

**SAMPLES
DELIVER TO**

NO. CARS PULLED
SAMPLED BY

NO. DRUMS 15
LUMP WGT. 2104
RELEASED BY 2

-GRINDING-

MILL 2 LSP 0.066" RP SCREEN 1750 RPM
MAX. TEMP. 150°F

SCREEN	RPM
MAX. TEMP.	°F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING

DATE MIXED

SAMPLES 2 ENV

DELIVER TO C T L

~~EXAMPLES BY~~

RELEASED BY

38442
124
51

Dump - 9 cars - 15 drums

0.00	0
1.56	+
0.14	-
1.60	+
0.14	-
1.58	+
0.14	-
1.62	+
0.14	-
1.74	+
0.14	-
1.64	+
0.14	-
1.67	+
0.14	-
1.63	+
0.14	-
1.62	+
0.14	-
1.60	+
0.14	-
1.61	+
0.14	-
1.67	+
0.14	-
1.69	+
0.14	-
1.42	+
0.14	-
0.49	+
0.14	-
21.04	*