

1. General

A representative sample of each shipment shall be sent by the vendor to the Johns-Manville Research Laboratory for test and approval before release of the shipment.

2. Standard Wet Screen Test

(a) The fibre shall conform to the following screen analysis:

<u>Screen</u>	<u>Percent</u>
+14 M	30 - 50
+28 M	0 - 13
+100M	0 - 16
+200M	0 - 16
-200M	36 - 56

(b) Rock and crud fibre on the +14M screen shall not exceed two percent.

3. Change in Material

No change in material shall be made by the vendor without written approval from Johns-Manville.

CONFIDENTIAL**AS A CH. FROMS PENDING**

Each vendor, or any change in material from an approved vendor, must be approved by the Local Quality Control Department and the Research Department. These approvals will be secured by the Purchasing Department.

PLAINTIFF'S
EXHIBIT

10841.0

I - change in number series

IMPORTANT: ALWAYS INCLUDE:

SPECIFICATION NUMBER WHEN REFERRING TO THIS COMMODITY

DATE PREPARED

SPECIFICATION CANCELLED BY THIS ISSUE

DATE EFFECT

JRM 5013-3
PRINTED IN U.S.A.

9-13-50

62625-1 M-W (1-17-50)

9-14-50