MD-3-A

PACKAGE TICKET

CODE Rt 539 LOT G2H-08

PO	NET WT/PKG.	NO. PKG.	PACK WT.	LOCATION
		4	411	24
	STUMP			

TOTAL NET WT. 411 Cant Explain Low yield

LUMP WT. 479 PKG. N-CODE

PROD. SUPV. RH DATE 9 26 82 OPERATOR 2-3

N32575

DUP050463645

PRODUCT NAME = NAPHTHANIL RED DARK SEMI-BLEEDING DATE PRINTED: 2/26/82

CG 40 CODE RT-539-D PKG ____

JUN 25 1982 G2H08

DATE LOT NUMBER

EST. WT. ~~474~~ 439* LBS. 4

12
105

PROCESSES APPROVED BY
RT-539-D (N) JJG 6/10/81
EWK12/2/81

TYPED BY JMH

MAKING NOTES _____

JOB NAME: 40RT539DPN

= PRESSING =

INSTRUCTIONS						RECORD					
VAT	105					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	6-28-82					STARTED	83				
TIME	5:10 pm					CAKES USED	32				
RELEASED BY	[illegible]					WATER ON	9.30 PM				
PRESS	12					HRS. WASHED	4				
NO.OF CAKES	32					M MHOS	250				
PRESS WITHOUT	AGITATION					HRS. WASHED					
WASH TO 250 M MHOS -	35-75 F WATER					M MHOS					
TEST AFTER 4 HOURS						HRS. WASHED					
LOAD ON 3 CARS						M MHOS					
						CAKE CONDITION					
						NO CARS LOADED					
						EXPLAIN LOSSES	2#1				

SAMPLES
~~DELIVER TO~~ CTL

SAMPLED BY
RELEASED BY [signature]

= DRYING =

DRY 20 HOURS AT 180 F

LUMP: ~~OK~~ - WET - SALTS - CONTAMINATD
DRYER SECTIONS USED: _____

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 8 oz
DELIVER TO

NO CARS PULLED
SAMPLED BY
RELEASED BY A.K

NO DRUMS 4
LUMP WGT 479

= GRINDING = (NOTE REVISION)

MILL #5 LSP .066 SCREEN 1750 RPM. PULVERIZE TWO TIMES.
DOUBLE PULVERIZATION HAS BEEN REQUESTED BY OPERATIONS.
DO NOT EXCEED 140 DEGREES FAHRENHEIT DURING GRINDING.
INERT MILL WITH CO2 WHEN GRINDING PER O.P.# O.F.0043.

EXPLAIN LOSSES : _____

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV
DELIVER TO CTL

DATE MIXED 7/24/82

SAMPLED BY 213
RELEASED BY

N32575.01

DUP050463646

8
51
16

0.00 *

1.57 +
0.14 -
1.57 +
0.14 -
1.51 +
0.14 -
0.70 +
0.14 -
4.79 *

N32575.02

DUP050463647