MD-3-A

PACKAGE TICKET

CODE HE 735 LOT F21C79

PQ	NET WT/PKG.	NO. PKG.	PACK WT.	LOCATION
6	2000	1	1	79
	1986	1	1	289
	STUMP			

TOTAL NET WT. 3986

LUMP WT. 3986 PKG. N-CODE

PROD. SUPV. DATE 7/1/82 OPERATOR

N37594

PRODUCT NAME = MOLYBDATE ORANGE NON-BLEEDING

CG 01 CODE YE-735-D PKG ____ | 91 / 245 PROCESSES YE-735-D (M) FWP 10/07/81 APPROVED BY

LOT **F2K79** JUN 18 1982 | ALTERNATE TYPED BY JMH

EST. WT. 3819* LBS. | MAKING NOTES _____

JOB NAME: 01YE735DPM

INSTRUCTIONS = PRESSING = RECORD

					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
VAT	245				STARTED	12 NN				
DATE	6-23				CAKES USED	42				
TIME	5:45AM				WATER ON	9:30AM				
RELEASED BY	OGH				HRS. WASHED	8				
PRESS	2	91			M MHOS	285				
NO.OF CAKES	32	42			HRS. WASHED					
PRESS WITH AGITATION SEE BELOW					M MHOS					
WASH TO 285 M MHOS WITH 35-75*F WATER.					HRS. WASHED					
TEST AFTER 2 HOURS.					M MHOS					
LOAD ON 5 CARS.					CAKE CONDITION					
STOP AGITATOR AT ABOUT 50*					NO CARS LOADED	5				
DO NOT EXTRUDE.					EXPLAIN LOSSES					

SAMPLES JAR — SAMPLED BY

DELIVER TO — RELEASED BY

= DRYING =

DRY 14 HRS AT 240*F MAY 1 - AUG. 31.

DRY 12 HRS AT 240*F SEPT. 1 - APR 30

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

NO DRUMS 13

LUMP WGT 3986

SAMPLES

DELIVER TO

NO CARS PULLED

SAMPLED BY

RELEASED BY

= GRINDING =

'MIKROATOMIZE

SET ROOF GATE AT 5 INCHES AIR FLOW.

MAGNEHELIC READING ON ATOMIZER PANEL BOARD _____ (1.0")

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING

SAMPLES 1 ENV & 2 PT. CANS

DELIVER TO CTL

DATE MIXED

SAMPLED BY

RELEASED BY

N37594.01

DUP050045896

5-ciu. Dumps
13 Dumo

79		⊠
124		⊠
41		⊠
330	+	
14	−	
324	+	
14	−	
328	+	
14	−	
330	+	
14	−	
323	+	
14	−	
345	+	
14	−	
332	+	
14	−	
345	+	
14	−	
352	+	
14	−	
316	+	
14	−	
317	+	
14	−	
330	+	
14	−	
196	+	
14	−	
3986	T	

DUP050045897