

CODE
LOT
NET WT/PKG.
NO. PKG.
PACK. WGT.
LOCATION
PO
STUMP
TOTAL NET WT.
PKG. N-CODE
PROD. SPVR.
DATE
WHSE. OPER.

N32381

8/5
247

CG 04 CODE KO-909-D PKG.
→ APR-28-35493
EST. WGT. 1674 LBS.

PROCESSING INSTRUCTIONS: BATCH UNI

PROCESSES	APPROVED B
KO-909-D (C)	EWK 1-27-
	DCG 1-30-
TYPED BY	
NSA 3-13-78	

MAKING NOTES

REMARKS

TOTAL WGT. 5274 (Req _____)

KROLOR® ORANGE Y — NON-BLEEDING

INSTRUCTIONS — -PRESSING- — RECORD

						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
E	247 1-30-80 5145 PM					STARTED	6 PM				
E						CAKES USED	46				
EASED BY						WATER ON	7 PM				
SS	22	22	23	24		HRS. WASHED	5½				
OF CAKES	46	46	46	52		OHMS	2500				
S with		AGITATION				HRS. WASHED					
TO 2000		OHMS with 135-145° water				OHMS					
AFTER 2		HOURS				HRS. WASHED					
on 6 cars						OHMS					
						CAKE CONDITION					
						NO. CARS LOADED	8				
						EXPLAIN LOSSES					
PLES 1-8 oz						SAMPLED BY		RELEASED BY			
VER TO CTL for color											

-DRYING-

22 HOURS AT 180°F

Dry on first stage only.
Reset every 3 hrs til dry.

LUMP: - OK - WET - SALTS - CONTAMINAT	
Lot appears dry.	
ADDITIONAL DRYING HOURS REQUIRED	
NO. DRUMS	19
NO. CARS PULLED	LUMP WGT. 5486
SAMPLED BY	RELEASED BY

3/3-2

-GRINDING-

938 HSP 1750 RP SCREEN 3500 RPM
TEMP. 170°F

SCREEN	RPM
MAX. TEMP.	°F
EXPLAIN LOSSES	
DATE MIXED	
SAMPLED BY	RELEASED BY

E / WITHOUT MIXING
LES 1-ENV & 1 PT CAN
CTL

DUP050457782

N32381.01

354.93 N
.41 N
.16 N
.00 T

3.19
.12
3.08
.12
3.00
.12
2.98
.12
2.94
.12
2.99
.12
2.95
.12
2.98
.12
3.23
.12
3.09
.12
2.93
.12
3.15
.12
3.12
.12
3.00
.12
3.05
.12
3.05
.12
2.97
.12
3.00
.12
2.44
.12
54.86 T

N32381.02

DUP050457783