MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KY-225-D LOT 34723

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
	1	2357	T-202	
	1	2260	T-101	
	STUMP			

TOTAL NET WT. 4617 PKG. N–CODE

PROD. SPVR.	DATE	WHSE. OPER.
CH	3/8/83	

N 26286

DUP050093695

22/244

CG 03 CODE KY-795-D PKG. ____

→ MAR-5 34723

EST. WGT. ~~1178~~ 1162 LBS. OK FP

Total Wgt: 4612

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-795-D (I)	EWK 10/6/76
Alternate	DCG 10/7/76
TYPED BY	
NE 3/3/77	

MAKING NOTES

REMARKS

NAME: "KROLOR" YELLOW-MEDIUM NON-BLEEDING

INSTRUCTIONS **-PRESSING-** **RECORD**

VAT	2H4				
DATE	3/6/80				
TIME	6.40Pm				
RELEASED BY	RM.				
PRESS	22	23	~~84~~	24	
NO. OF CAKES	46	46	~~46~~	52	

PRESS with AGITATION
WASH TO 5000 OHMS
TEST AFTER 5 HOURS with 35-75°F water
LOAD on 5 cars

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	7PM				
CAKES USED	46				
WATER ON	1Pm				
HRS. WASHED	12				
OHMS	5000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	6				

EXPLAIN LOSSES

SAMPLES 1-8 oz JAR
DELIVER TO ctl for color

SAMPLED BY 4601 RELEASED BY

-DRYING-

Dry 16 Hrs. at 220°F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

No Drums : 15

SAMPLES
DELIVER TO

NO. CARS PULLED LUMP WGT. 4686
SAMPLED BY RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 210 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 Env & 1 Pt Can
DELIVER TO CTL

DATE MIXED

SAMPLED BY RELEASED BY

DUP050093696

N 26286.01

34723
41
354
6

0.00	*
3.37	+
0.14	-
3.35	+
0.14	-
3.31	+
0.14	-
3.25	+
0.14	-
3.27	+
0.14	-
3.25	+
0.14	-
3.36	+
0.14	-
3.35	+
0.14	-
3.45	+
0.14	-
3.52	+
0.14	-
3.67	+
0.14	-
3.55	+
0.14	-
3.57	+
0.14	-
2.80	+
0.14	-
1.89	+
0.14	-
46.86	*

DUP050093697