

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE

15795

LOT

36168

NET WT/PKG

NO. PKG

PACK. WGT

LOCATION

PQ

2350

1

T-114

2220

1

T-273

STUMP

Lump 11595

TOTAL NET WT.

12.10

PKG. N-CODE

PROD. SPVR.

DATE

WHSE. OPER.

ST

6/12/79

N32146

DUP050456815

CG 03 CODE KY-795-0 PKG

JUN 17 36160

EST. WGT. 880 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY 795-D (1)	EWK 10/6/76
Alternate	DCG 10/7/76

TYPED BY

NE 3/3/77

emw031579 MAKING NOTES FWP 03-15-79

REMARKS

Total Wgt: 4630

NAME: "KROLOR" YELLOW-MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

AT	244					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	6-18-80					STARTED					
TIME	12:05 PM					CAKES USED					
RELEASED BY	C. H.					WATER ON					
RESS	22	23	24	25		HRS. WASHED					
J. OF CAKES	46	46	46	52	48	OHMS	5000				
RESS with						HRS. WASHED					
ASH TO	5000					OHMS					
EST AFTER	5					HRS. WASHED					
OAD	on 5 cars					OHMS					
						CAKE CONDITION					
						NO. CARS LOADED					
						EXPLAIN LOSSES					

MPLES 1-8 oz JAR
 ELIVER TO Ctl for color

SAMPLED BY

RELEASED BY

-DRYING-

Dry 14 Hrs at 220°F

LUMP: - OK - WET - SALTS - CONTAMINATE

NOTE: If dried in 12-23, 80-97, or
 138-155 sections;

- dry for 14 hrs at 220°F
- record sections:
- fill in additional hrs
 required if any:

ADDITIONAL DRYING HOURS REQUIRED

MPLES
 ELIVER TO

NO. CARS PULLED
 SAMPLED BY

No. Drip

LUMP WGT.
 RELEASED BY

GRINDING.

LL 930 HSP 3/32" RP SCREEN 3500 RPM
 MAX. TEMP. 210 °F

SCREEN
 MAX. TEMP.

1100 RPM
 °F

MPLE WITHOUT MIXING

MPLES 1 Env & 1 Op Can
 ELIVER TO Ctl

DATE MIXED

SAMPLED BY

RELEASED BY

N32146.01

DUP050456816

35163

41

225

0.00 *
3.95 +
0.14 -/
3.80 +
0.14 -/
3.85 +
0.14 -/
3.92 +
0.14 -/
3.86 +
0.14 -/
3.65 +
0.14 -/
3.75 +
0.14 -/
3.70 +
0.14 -/
3.71 +
0.14 -/
3.77 +
0.14 -/
3.85 +
0.14 -/
3.75 +
0.14 -/
2.21 +
0.14 -/
15.95 *

N32146.02

DUP050456817