

January, 1972

PLI-132

PLICAST LWI-24GFormula

5m Bat Grog	25%
8m L.W. Grog	31%
Perlite	4%
Lumnite Cement	40%
	<u>100%</u>

Ingredients

Bat Grog: Passing a 5 X 5 X 0.063" dia. wire screen
and retained on a 50 X 50 X 0.010" dia.
wire screen.

Perlite: Passing an 8 X 8 X 0.063" dia. wire screen.
Local source.

Cement: from Atlas Co. in 94# bags.

Mixing

Dry ingredients thoroughly mixed and packed in
100# bags.