

- 17 -

RECEIVED BY THE UNITED STATES DEPARTMENT OF THE ARMY
 Formed by three manufacturers in Chicago, January 1941 - June 1942

Lithophone (701)

Percentage Formula

Working or Vat Formula

January 1941 to May 1942 2/

January 1941 to May 1942

Percent

Gals. Lbs.

35.5

Lithophone

400

64.5

Lithophone Mixing Varnish 92

100.0

Colligan Zinc Drier 18

Intense Drier 2

June 1942 2/

June 1942

Percent

Gals. Lbs.

35.5

Lithophone

400

64.5

Lithophone Mixing Varnish 92

100.0

Colligan Zinc Drier 18

Intense Drier 2

Red Barn Paint (702)

Percentage Formula

Working or Vat Formula

January 1941 to June 1942 2/

January 1941 to June 1942

Percent

Gals. Lbs.

55.3

Venetian Red

250

44.7

Actronite

250

100.0

Asbestine

200

Brown Soya Bean Oil 10

Raw Linseed Oil 13

Gloss Oil 24

Clean Spirits 14

Intense Drier 4

Solution 1

Cobalt Drier 2

Taken from working formula.