




Schneider Laboratories, Inc.

1508 W. MAIN STREET • RICHMOND, VA 23220 • (804) 353-6778

ASBESTOS IDENTIFICATION REPORT
[BY EPA INTERIM METHOD]
[40 CFR 763, SUBPT F, APP. A]

PLAINTIFF'S
EXHIBIT

G-425

CLIENT: Robert R. Hatten, Esq. LABORATORY NO: 336-339
ADDRESS: Patten, Wornom ACCOUNT NO. 0M-88-05
CITY/STATE/ZIP Newport News, Va. DATE RECEIVED: 3/06/88
23606

THE SAMPLE(S) SUBMITTED FOR ASBESTOS BULK ANALYSIS HAVE BEEN COMPLETED.
THEY WERE ANALYZED BY POLARIZED LIGHT MICROSCOPY WITH DISPERSION STAINING.


	SAMPLE #	SAMPLE #	SAMPLE #	SAMPLE #
I. LABORATORY NO.	336	337	338	339
FIELD I.D. NO.	Garlock 900	Gar 7021	Gar 7228	Gar 7021 (1/32")
II. RESULTS: ASBESTOS PRESENT	yes	yes	yes	yes
III. TYPE ASBESTOS (IF PRESENT)				
A. CHRYSOTILE	90%	90%	90%	85%
B. AMOSITE				
C. CROCIDOLITE				
D. ANTHOPHYLLITE				
E. FIBROUS TREMOLITE				
F. FIBROUS ACTINOLITE				
APPROXIMATE PER CENT ASBESTOS	90%	90%	90%	85%
IV. ASSOCIATED FIBROUS MATERIALS				
A. CELLULOSE FIBER	10%	10%	10%	15%
B. FIBROUS GLASS				
C. SYNTHETIC FIBER				
V. NONFIBROUS MATERIALS				
A. GYPSUM				
B. CALCITE				
C. SILICA				
VI. REMARKS				
[DETECTION LIMIT]				
[< 1% ASBESTOS]				

ANALYST: R. ABOUZAKI

DATE OF ANALYSIS: 3/06/88

REVIEWED & APPROVED: R. VANCE, Ph.D.; LABORATORY DIRECTOR

Rafa Abouzaki
2 Vance 3/6/88



Schneider Laboratories, Inc.

1508 W. MAIN STREET • RICHMOND, VA 23220 • (804) 353-6778

LABORATORY ANALYSIS REPORT
ASBESTOS FIBER COUNT BY NIOSH 7400 METHOD

AIHA/EPA ACCREDITED

ACCOUNT: OM-88-05

DATE COLLECTED: 3/06/88

DATE RECEIVED: 3/06/88

CLIENT: Robert R. Hatten

DATE REPORTED: 3/06/88

ADDRESS: Patten, Wornom & Watkins
Newport News, VA 23606

CUS. PURCH. ORD.

AIRBORNE FIBER CONCENTRATIONS INSIDE GLOVEBOX

FIELD SAMPLE NO.	SCHN LAB SAMPLE NO.	TOTAL FIELDS COUNTED	FLOW RATE l/min	FIBER COUNT PER FIELD	TOTAL TIME SAMPLE COLL'D (min)	SAMPLE VOLUME (l)	ACTUAL EXPOSURE (f/cc)
Crane 333	333	40	3	2.875	15	45	3.1
Garlock 7228	331	40	3	2.838	21	63	2.2
Garlock 7021	335	100	3	0.31	8	24	0.6

MICROSCOPIC FIELD AREA (MM²): 0.00785

ANALYZED BY R. ABOUZAKI

Rafa Abouzaki 3/6/88

REVIEWED BY R. VANCE, Ph.D., LABORATORY DIRECTOR

R Vance 3/6/88