MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KY-287 LOT 37927

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
1650	1	T= 202		
1630	1	T= 137		
	STUMP	LUMP 3268		

TOTAL NET WT. 3280 PKG. N–CODE

PROD. SPVR. DATE WHSE. OPER.

11/22/85

N34818

23/240

CG 03 CODE KY-787-D PKG. ____

→ NOV 17 80 37927

EST. WGT. 1090 LBS.

OK/KP

TOT. WGT. 3332#

PROCESSING INSTRUCTIONS: BATCH UNIT

14

PROCESSES	APPROVED BY
KY-787-D (Q)	EWK 9/22/76
	DCG 9/27/76
RETYPED BY	
CJH 4/2/80	

MAKING NOTES

REMARKS

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

-PRESSING-

INSTRUCTIONS						RECORD					
VAT	240					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	11-19-80					STARTED	5:30PM				
TIME	4:31					CAKES USED	46				
RELEASED BY	MD					WATER ON	1230AM				
PRESS	22	23	24	25		HRS. WASHED	3				
NO. OF CAKES	46	46	52	48		OHMS	5000				
PRESS WITH		AGITATION				HRS. WASHED					
WASH TO 2000		OHMS WITH 35-75 F WATER				OHMS					
TEST AFTER 2		HOURS				HRS. WASHED					
LOAD ON 6 CARS						OHMS					
						CAKE CONDITION					
						NO. CARS LOADED	6				
						EXPLAIN LOSSES					

AR

SAMPLES 1-8 OZ JAR

DELIVER TO CTL FOR COLOR

SAMPLED BY RELEASED BY

-DRYING-

DRY 12 HRS AT 220 °F

THEN DRY 6 HRS AT 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 14

SAMPLES

DELIVER TO

NO. CARS PULLED

LUMP WGT. 3268

SAMPLED BY

RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM

MAX. TEMP. 150 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING

SAMPLES 1 ENV & 1 PT. CAN

DELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

DUP050105387

3332

(64)



DUP050105389