CODE Ky-908 LOT B1033

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
1840	1	T	205	
1870	1	T	55	
	STUMP	3705#		

TOTAL NET WT. 3710 PKG. N–CODE

PROD. SPVR. DATE WHSE. OPER.

5.14.81

PRODUCT NAME = KROLOR YELLOW-LIGHT

NON-BLEEDING

CG 03 CODE KY-908-D PKG ____

D 10 33

LOT MAY-0·81-[illegible]3 OK

EST'D WGT 1603 LBS

TOTAL EST'D WGT=~~[illegible]~~ 3549 LBS (CRT ENTRY)

PROCESSES APPROVED BY
KY908D(F) FWP 01/27/81
ALTERNATE
TYPED BY WRT/JMW

MAKING NOTES

JOB NAME: 03KY908DPF

---

262 INSTRUCTIONS (Vim) = PRESSING =

VAT					
DATE 4-24-81					
TIME 5:30					
RELEASED BY					
PRESS	96	95			
NO.OF CAKES	72	~~72~~ 40			

PRESS WITH AGITATION
WASH TO 2000 OHMS - 135-145 F WATER
TEST AFTER 3 HOURS
LOAD ON ~~10~~ CARS

SAMPLES 8 OZ JAR
DELIVER TO CTL FOR COLOR

RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED					
CAKES USED					
WATER ON	1632				
HRS. WASHED	3260				
OHMS					
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO CARS LOADED	6				

EXPLAIN LOSSES

SAMPLED BY
RELEASED BY

= DRYING =

DRY 24 HOURS AT 180 F
NOTE: DRY ON FIRST STAGE ONLY.
RE-SET ON FIRST STAGE TIL DRY.

SAMPLES
DELIVER TO

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

NO DRUMS 14
LUMP WGT 3705

NO CARS PULLED
SAMPLED BY
RELEASED BY

= GRINDING =

MILL 939 HSP 1/8"RP SCREEN 3500 RPM
MAX. TEMP. 170 F

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV & 1 PT CAN
DELIVER TO CTL

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

DATE MIXED

SAMPLED BY
RELEASED BY

DUP050096273

1033
41
305

0.00 *

2.73 +
0.12 -
2.92 +
0.12 -
2.93 +
0.12 -
2.75 +
0.12 -
3.01 +
0.12 -
2.90 +
0.12 -
2.76 +
0.12 -
2.16 +
0.12 -
21.20 *

21.20 +
2.90 +
0.12 -
2.86 +
0.12 -
2.96 +
0.12 -
3.08 +
0.12 -
2.90 +
0.12 -
1.99 +
0.12 -
[illegible] -
37.05 *

DUP050096274