MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE AT880 LOT 36382

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
	10	1867	20	
	STUMP Lumber		1850	

TOTAL NET WT. 1867 PKG. N-CODE

PROD. SPVR.	DATE	WHSE. OPER.
[illegible]	7/31	392

N37447


O.T
206.+
191.+
205.+
206.+
195.+
203.+
212.+
212.+
199.+
38.+
1867.T

CG 32 CODE RT-880-D PKG. ____

→ JUL 3 '80 36382

EST. WGT. 1921 LBS.

37/903

(10)

2 (98)

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
RT-880-D (E)	JJG 08-16-78
	AMJ 01-22-79
TYPED BY	
emw013179	

MAKING NOTES

REMARKS

NAME: WATCHUNG® RED B

NON-BLEEDING

-PRESSING-

INSTRUCTIONS						RECORD					
VAT	903					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	7-3-80					STARTED	10:00				
TIME	10:30					CAKES USED	60				
RELEASED BY	[illegible]					WATER ON	5AM				
PRESS	37					HRS. WASHED	8				
NO. OF CAKES	60					OHMS	7000				
PRESS	without	AGITATION				HRS. WASHED					
WASH TO	3000	OHMS with 35-75°F water				OHMS					
TEST AFTER	6	HOURS				HRS. WASHED					
LOAD	on 8 cars					OHMS					
	Press Immediately Code					CAKE CONDITION					
	Instruct Making Area to add 10# N-588-A					NO. CARS LOADED	741				
	half-way thru Pressing					EXPLAIN LOSSES					
	Clean Magnetic Separator after Pressing										
	Cleaned By: 469 Time Cleaned: 5A										
SAMPLES											
DELIVER TO						SAMPLED BY		RELEASED BY			

-DRYING-

Dry 20 Hrs at 220°F
Hold on track 30 min before
dumping pans

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 10

SAMPLES

NO. CARS PULLED

LUMP WGT. 1860

DELIVER TO

SAMPLED BY

RELEASED BY

-GRINDING-

MILL 2 LSP 1/8" RP SCREEN 1800 RPM

MAX. TEMP. 210°F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING

SAMPLES 2 Env & 1 Pt Can

DELIVER TO C T L

DATE MIXED 7-11-80

SAMPLED BY 389

RELEASED BY

N37447.01

DUP050042068

36332
5100
158

0.00 *

1.94 +
0.14 -
1.92 +
0.14 -
2.00 +
0.14 -
2.09 +
0.14 -
2.06 +
0.14 -
1.91 +
0.14 -
2.05 +
0.17 -
2.01 +
0.14 -
2.11 +
0.14 -
16.80 *

225

0.00 *

16.80 +
1.92 +
0.12 -
18.60 *

DUP050042069