MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE XT808 LOT 38129

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
	15	2229	56	
	STUMP	Lump	221C	

TOTAL NET WT. 2229 PKG. N–CODE

PROD. SPVR. DATE WHSE. OPER.

12/11 352

N37566

#1 MEMBRANE 106 Vat

CODE YT-808-D PKG.

→ DEC -8 80 38179

EST. WGT. 2238 LBS.

83°
177° Temp — — — 2 gs

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
YT-808-D (D)	EWK 9/28/77
	BBK 10/17/77
	DCG 10/17/77
TYPED BY	
JJC 10/26/77	

MAKING NOTES

REMARKS

AME: DALAMAR® YELLOW

BLEEDING

INSTRUCTIONS					-PRESSING- RECORD						
AT				106	PRESSLOAD	1ST	2ND	3RD	4TH	5TH
ATE				12-8-80	STARTED	9:15 AM				
IME				3:30 AM	CAKES USED	62				
ELEASED BY					WATER ON	11:30 AM				
RESS	32	33	35	M1	HRS. WASHED	4½		1		
O. OF CAKES	60	62	60	62	OHMS	4500				
RESS	WITHOUT	AGITATION			HRS. WASHED			1		
ASH TO	4000	OHMS with 35-75°F water			OHMS					
EST AFTER	4	HOURS			HRS. WASHED					
OAD	on 9 cars				OHMS					
					CAKE CONDITION					
					NO. CARS LOADED	6				
					EXPLAIN LOSSES					
					Record: Vat TEMP 122 °F					
AMPLES										
ELIVER TO					SAMPLED BY		RELEASED BY			

-DRYING-

DRY 24 HOURS AT 200°F	LUMP: - OK - WET - SALTS - CONTAMINATED
	ADDITIONAL DRYING HOURS REQUIRED
	NO. DRUMS 14
AMPLES	NO. CARS PULLED — LUMP WT. 2216
ELIVER TO	SAMPLED BY — RELEASED BY BLL

-GRINDING-

ILL 4 or 10 HSP 1/8"RB SCREEN 3500 RPM	SCREEN — RPM
AX. TEMP. 190 °F	MAX. TEMP. — °F
	EXPLAIN LOSSES
AMPLE WITHOUT MIXING	DATE MIXED
AMPLES 1 env + 1 Pint can	
ELIVER TO C T L	SAMPLED BY — RELEASED BY

N37566.01

DUP050045814

38179

124
51

1.84 +
0.14 -
1.67 +

0.14 -
1.74 +
0.14 -
1.70 +
0.14 -
1.70 +
0.14 -
1.72 +
0.14 -
1.77 +

0.14 -
1.68 +

0.14 -
1.68 +
0.14 -
1.68 +

0.14 -
1.75 +
0.14 -
1.79 +
0.14 -
1.65 +

0.14 -
1.75 +
0.14 -
22.16 *

DUP050045815