

FORMULA RECORD			Exp. No. _____ Date <u>2-25-42</u> Class _____ Rex. No. <u>B-1</u>	
Name <u>Rustic Shingle Stain Lt. Green</u>			Card No. <u>6</u>	See No. _____
# POUNDS	GALLONS	MATERIAL NO.	Customer	Trade in General
<u>114</u>		<u>11834</u>	To Match	<u>Standard</u>
<u>3</u>		<u>412</u>	Reason for Revision	<u>Change to avail-</u>
<u>2</u>		<u>547</u>		<u>able greens</u>
<u>123</u>		<u>(2)</u>		
<u>4</u>		<u>(12)7</u>		
			Viscosity <u>9"</u> <u>75deg.</u> <u>#2</u> at _____ hrs. after grind	
			Viscosity _____ at _____ hrs. after grind	
<u>79</u>		<u>(2)</u>	Wt./Gal. <u>8.11</u>	Label Analysis Checked-Date _____
<u>29</u>		<u>(185)</u>	Baume _____	Label: No Red ☐ ; Red ☐
<u>251</u>		<u>(141)</u>	Std. of Fineness <u>3M</u>	New Std. Sample Required _____
<u>212</u>	<u>(2024) or</u>	<u>(141)</u>	Normal Output <u>100</u>	Date Rec'd _____
<u>9</u>		<u>(2511)</u>	Est. Mfg. Loss <u>2%</u>	Mill _____
			Department _____	Lbs. or Gals. per hour _____
			Parallel No's _____	Approved _____
				Formulator <u>G.D.</u>
				Supt. <u>76</u>

MANUFACTURING INSTRUCTIONS			FACTORY		
			DATE	SLIP NO.	AMOUNT
APPLICATION: SURFACE <u>Masonry</u>					
NO. COATS <u>7</u>					
UNDERCOATER USED			FACTORY	FORMULA	SPEC. CARD
METHOD 1 <u>Brush</u>			EXEC. COST DEPT.		
REDUCTION: AMOUNT <u> </u> REDUCER USED <u> </u>			CLEVELAND		
METHOD 2 <u> </u>			KENSINGTON		
REDUCTION: AMOUNT <u> </u> REDUCER USED <u> </u>			ALLIED RESEARCH		
			KENS. TECH. SERV.		
			KENS. LACQUER		
			NEWARK		
DRYING TIME: TOUCH <u>7 hrs</u> RECOAT <u>48 hrs</u> STENCH			OAKLAND		
HARD <u> </u> SAND <u> </u> HANDLE <u> </u>			H. SENOUR		
TACK FREE <u> </u> RUB <u> </u> WRAP <u> </u>			DETROIT		
BAKING TIME AND TEMP. <u> </u>			LOS ANGELES		
GLOS <u>Eggshell</u> FILM <u>Hard & Tough</u>			DALLAS		
SPECIAL TESTS <u> </u>			DAYTON		
			GIDDSEORO		
			EXEC. MFG.		
			CUBA		
			MONTREAL		
			BUENOS AIRES		
			BRAZIL		
			REG ADM		
			MEXICO		

0007-SWP-061040

FORMULA RECORD			
Exp. No.	Date	Class	Ref. No.
Name	5-27-41		B-1
Rustic Shingle Stain Light Green		Card No.	5
See No.			
120	LBS.	1025	Customer
3	"	412 or 412E	Trade in General
2	"	547	To Match
123	"	(3014)	Standard - Same AS Rx 763.
4	"	(12)W	Weight Per Gal. 18.02
	"		Visc. 9" 75 deg. #2 cup
	"		Baume
	"		Std. of Fineness 3M
	"		No Label Required
247	"	Paste Wt	Mill
79	"	(3014)	New Std. Sample Required
29	"	(183)	NO
250	"	(141)	Date Rec'd.
200	"	(2024) or (141)	Reason for Revision
9	"	(2511)	Replacing 108X with 412.
Trace	"	LY	
	"		
	"		Normal Output 100
	"		Approved
	"		Est. Mfg. Loss 2%
	"		Formulator
	"		Department
	"		Supt.
	"		Label Analysis Checked-Date

A 135 9-40 5-75

MANUFACTURING INSTRUCTIONS				114		
Finish product is 1H as contracted to the 4" required for ground parts.				DATE	SLIP NO.	AMOUNT
APPLICATION: SURFACE Galvanized Iron						
NO. COATS						
UNDERCOATER USED				FACTORY	FORMULA	SPEC. CARD
METHOD 1 Brush				EXEC. COST DEPT.		
REDUCTION AMOUNT 25% REDUCER USED (348)				CLEVELAND	A	
METHOD 2				KENNINGTON	C	
REDUCTION AMOUNT				ALLIED RESEARCH		
REDUCER USED				KENS. TECH. SERV.		
				KENS. LACQUER		
				NEWARK	H	
Drying Time Touch 3-6 hrs Recoat 24 hrs				OAKLAND	D	
				M. SENOVA	H	
WASH SAND HANDLE				DETROIT	B	
TACK FREE RUB WRAP				LOS ANGELES	P	
Drying Time and Temp				DALLAS	T	
Color Eggshell Film Hard & Elastic				DARTON	I	
				GOODSON	T	
				ST. LOUIS		
				CUBA	H	
				MONTREAL	C	
				BUENOS AIRES	Z	
				BRASIL	S	
				TIERRA		
				MEXICO		