

MO-8-A

PACKAGE TICKET

CODE

BP565

U. LOT

L2J83

PQ

NET WT/PKG.

NO. PKG.

PACK WT.

LOCATION

8

11.32

15

STUMP

TOTAL NET WT.

11.32

LUMP WT.

11.63

PKG. N-CODE

PROD. SUBV.

DATE

OPERATOR

11/19

292

0.0

1.40 +

1.41 +

1.34 +

1.43 +

1.47 +

1.38 +

1.51 +

1.38 +

008

11.32 ±

DUP050060643

N41202.01

PRODUCT NAME = MONASTRAL BLUE B
(RESIN EXTENDED CPC FOR PLASTICS)
CG 20 CODE BP-565-D PKG -----

NON-BLEEDING

PROCESSES APPROVED BY
BP-565-D (A) BBK 11/20/81
XOC-23 TCP 07/02/82

LOT 12J83

(8)

p/c
9

EST. WT. 1333 LBS.

MAKING NOTES

JOB NAME: 20BP565DPA

N-099AB, 1333M, 2 boxes

INSTRUCTIONS

= PRESSING =

RECORD

VAT	DATE	TIME	RELEASED BY	PRESS	NO. OF CAKES	PRESS WITH AGITATION	WASH TO OHMS -	TEST AFTER HOURS	LOAD ON 8 CARS	PANLOAD	PRESSLOAD	STARTED	CAKES USED	WATER ON	HRS. WASHED	OHMS	HRS. WASHED	OHMS	HRS. WASHED	OHMS	CAKE CONDITION	NO CARS LOADED	EXPLAIN LOSSES
* USE BP-565 CARS ONLY																							

SAMPLES JAR
DELIVER TO

SAMPLED BY
RELEASED BY

36
DRY HOURS AT 180 DEG F.
DRY IN SECTIONS:

= DRYING =

LUMP: - OK - WET - SALTS - CONTAMINATED

* TAKE COMPOSITE SAMPLE FROM EACH DRYER CAR. NOTE CODE, LOT, DRYER #, DATE, TIME
* DELIVER TO CTL FOR % MOISTURE IF % MOISTURE LESS THAN 1% - OK TO PULL
LOCK LID
* DUMP IN NEW - USED LPS

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS
LUMP WGT 1163

1/8
MILL LSP SCREEN 1700 RPM
MAX. TEMP 140 DEG F
PULVERIZE WITH DRY ICE
STORE WITH LOOSE LID - 3-4 HRS.
(ALLOWS DRY ICE TO ESCAPE)

= GRINDING =

SCREEN RPM
MAX. TEMP. F

* PULVERIZE WITHOUT HAMMERS
* GRIND WITH CO₂ AS PER OP# FA 0043

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 2 ENV & 2 PT CAN
DELIVER TO CTL

DATE MIXED
SAMPLED BY
RELEASED BY

200 11-19-82

83
51
16

0.00 *

1.56 +

0.14 -

1.42 *

8.29 +
1.49 +
0.14 -
1.55 +
0.14 -
0.72 +
0.14 -
11.63 *

1.42 +

1.68 +

0.14 -

1.66 +

0.14 -

1.61 +

0.14 -

1.63 +

0.14 -

0.99 +

0.14 -

8.29 *