

AUG 15 1980

MAKING INSTRUCTIONS: BATCH UNIT

S V

C V

D V

CG 40 CODE ~~RT-160P~~ PKG

→ AUG 20 80 36879

EST WGT

LBS

STD HRS

TIME

M

PROCESSES

APPROVED BY

(RT-160P)

(RT-531-D)

()

()

TYPED BY

(RT160P 33232 DRYOUT 86#NET 34.29 SOLIDS)

Total Wgt - 29#

160-12#

NON-BLEEDING

EQUIPMENT

NAME:

USE
LBSN
CODEACCT
LBS

DUD050100000

CG 40 CODE ~~RT-531-D~~ RT-531-D PKG. _____

→ AUG 20 80 36879
EST. WGT. ~~655~~ 0 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

RT-531-D	PROCESSES RT-531-D (N)	APPROVED BY BBK 04-25-7
	RT-531-D	DCG 04-26-7
	TYPED BY emw042977	
	MAKING NOTES	

REMARKS

Total Wgt - 29#

NAME: NAPHTHANIL® RED LIGHT

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE						STARTED					
TIME						CAKES USED					
RELEASED BY						WATER ON					
PRESS	12	26				HRS. WASHED					
NO. OF CAKES	36	40				OHMS					
PRESS without						HRS. WASHED					
WASH TO	4000					OHMS					
TEST AFTER	2					HRS. WASHED					
LOAD on 3 cars						OHMS					
						CAKE CONDITION					
						NO. CARS LOADED					
						EXPLAIN LOSSES					

SAMPLES

DELIVER TO

SAMPLED BY

RELEASED BY

-DRYING-

Dry 24 hrs. at 160°F

LUMP: - OK - WET - SALTS - CONTAMINATED
Dryer sections used:

ADDITIONAL DRYING HOURS REQUIRED

No. Drums:

SAMPLES

DELIVER TO

NO. CARS PULLED

LUMP WGT.

SAMPLED BY

RELEASED BY

-GRINDING-

MILL #4 LSP 1/8" R^P SCREEN 2300 RPM
MAX. TEMP. 150°F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING

DATE MIXED

SAMPLES 1 Env & 1 Pt Can

DELIVER TO CTL

SAMPLED BY

RELEASED BY