PLAINTIFF'S EXHIBIT
KM-391

PACO TEXTURES MEMO

TO: Svend Stubb FROM: Doug Merrill June 5, 1978

SUBJECT: PACO PRODUCTS

Bill Freeman reports that the V-100G (San Carlos type) is better than the former V-100B Ceiling Texture, but is still hard to wipe off the walls. We are preparing one batch of V-100G with a reduction of B-28 (Sodium CMC Gum), at Hurst. This will be sent to Bill for evaluation.

We are still waiting for the Narvon from Hurst to make the 4051A Ready Mix that is now standard for Hurst and Broken Arrow. Bill Freeman says that the "A" is breaking down in viscosity under application. I am sending Ronnie Witaker some Magnesium Oxide which should correct this problem as it has in our formula at San Carlos.

DWM/jlb