

5, 7, 8 D

22

Lot 35610

240 CG 03 CODE KY-795-D PKO.

EST. WGT. 880 1178 1110 LBS.

MAY-1
OK
HP

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-795-D (I)	EWK 10/6/76
Alternate	DCG 10/7/76

TYPED BY
NE 3/3/77

MAKING NOTES

REMARKS

Total Wgt: 4878# 4380

NAME: "KROLOR" YELLOW-MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT	240					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	5-2-80					STARTED	8 PM				
TIME	5:10 PM					CAKES USED	50				
RELEASED BY	HP					WATER ON	120 min				
PRESS	22	23	24	24		HRS. WASHED	5				
NO. OF CAKES	46	46	46	52		OHMS	5000				
PRESS WITH						HRS. WASHED					
WASH TO	5000					OHMS					
TEST AFTER	5					HRS. WASHED					
LOAD	on 5 cars					OHMS					
						CAKE CONDITION	5				
						NO. CARS LOADED	5				
						EXPLAIN LOSSES					

SAMPLES 1-8 oz JAR
 DELIVER TO CCL FOR COLOR

SAMPLED BY

RELEASED BY

-DRYING-

Dry 16 Hrs. at 220°F

LUMP: - OK - WET - SALTS - CONTAMINATED

color appears DRY

ADDITIONAL DRYING HOURS REQUIRED

No Drums: 14

SAMPLES
 DELIVER TO

NO. CARS PULLED
 SAMPLED BY

LUMP WGT. 452.1
 RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
 MAX. TEMP. 210 °F

SCREEN RPM
 MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
 SAMPLES 1 Env & 1 Pt Can
 DELIVER TO C T L

DATE MIXED

SAMPLED BY

RELEASED BY

DUP050456395

N32050.01

356.10 N C

.41 N

2.31 N

.00 T

3.15 C

.12 -

3.55

.12 -

3.50

.12 -

3.25

.12 -

3.45

.12 -

3.45

.12 -

3.25

.12 -

3.30

.12 -

3.35

.12 -

3.34

.12 -

3.40

.12 -

3.35

.12 -

3.40

.12 -

3.15

.12 -

45.21 T