

Characteristics and Method of Using		Cost Data			Customers
Type of Goods					All plants 1-23-45
Color					
Luster					
Match for					
Kind of Reducer					
Amount of Reduction for					
Brushing					
Spraying	Pressure				
Dipping	Drip Time	Pigment 64 Analysis			
Floccing	Drip Time	Vehicle 36			
Tumbling		Pigment			
Air dry to recoat		35% leading zinc			51.6
To Sand or Rub		Lithopone			27.2
Bake Time	Temp.	Barium Sulphate			10.8
Rub with		Mag. Silicate			10.4
Polish with					
Schedule		Vehicle			
		Raw Linseed Oil			33.4
		Boiled " "			33.7
		Liquid Drier			6.1
		Minn. Spirits			26.8
					100.00%

GLD058999