106

CG 46 CODE YC-13-A PKG.

→ ~~DEC 28 80~~ 38385 JAN 5 1981

EST. WGT. 2736 LBS.

99s

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
(B) YC-13-A	EWK 10/4/76
	DCG 10/6/76
TYPED BY	
NE 3/8/77	

MAKING NOTES

REMARKS

AME: "DALAMAR" YELLOW - R E.C.

BLEEDING

INSTRUCTIONS —PRESSING— RECORD

AT				106	
ATE				1-8	
IME				215	
ELEASED BY				SH	
RESS	32	33	35	KH	
O. OF CAKES	60	62	60		

RESS without AGITATION

ASH TO 4000 OHMS with 35-75°F water

EST AFTER 4 HOURS

OAD In metal drums at 325# net per Drum

Air blow presscake 15 min at 40 PSI

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	1 Pm				
CAKES USED	60				
WATER ON	6P				
HRS. WASHED	6				
OHMS	5600				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED					

EXPLAIN LOSSES

AMPLES ~~2 QT JAR~~ 1 qt-RWD

ELIVER TO ctl for color

SAMPLED BY RELEASED BY

—DRYING—

LUMP: - OK - WET - SALTS - CONTAMINATE

Do not Dry

ADDITIONAL DRYING HOURS REQUIRED

MPLES

LIVER TO

NO. CARS PULLED LUMP WGT.

SAMPLED BY RELEASED BY

—GRINDING—

LL	SCREEN	RPM	SCREEN	RPM
X. TEMP.	°F		MAX. TEMP.	°F

EXPLAIN LOSSES

MPLE AFTER / WITHOUT MIXING

PLES

IVER TO CTL

DATE MIXED

SAMPLED BY RELEASED BY