

Lucobwik Enamel
Interior Trim Enamel
White
P.H.W.
First

				Actual 3/31/42		Market 3/31/42	
<u>Pigment</u>							
461-S	Lithopone	1652	46.256	3.95	65.25	4.40	72.69
2030	Titanium Oxide	1200	37.080	14.57	178.44	14.80	177.60
547	Aluminum Stearate	12	1.320	25.22	3.03	25.00	3.00
<u>Vehicle</u>							
(2848)H	-Grind & Mix Veh.	3663	499.633	8.49	310.97	10.46	383.16
(348)	Mineral Spirits	240	32.832	1.55	3.72	1.50	3.60
(4092)	Drier	18	2.239	32.04	5.77	21.00	5.58
(4091)	Drier	36	4.330	13.84	4.98	16.25	5.85
(2231)	Drier	90	11.844	3.27	2.94	8.55	7.70
(5026)	Anti-Skinning Agent	72	10.821	24.50	17.64	24.50	17.64
				592.74		676.81	

6983 649.355 93.31 106.54

649.355
2.17%
636.25

XXXXXX

.933 1.0
.025 .0
.056 .0
1.014 1.1
.187 .1
1.201 1.3

C.L. S.C.L.
3.09 3.25
2.62 2.76
3.09 5.25
3.09 3.25
3.42

OVER 500.
UNDER 500.

OPA EE000753

N 4761