

DE NAME: ARMSTRONG QUICK-DRY ENAMEL
 EGOY: INTERIOR ENAMEL
 OR: WHITE
 BER: 836
 LITY: FIRST

BS.	GALS.			
ment			30%	
227	7.03	Titanium Dioxide	1475	33.483
40	1.52	" Calcium	0575	2.300
50	1.4	Lithopone	045	2.250
icle			70%	
57.5	81.83	Varnish	696	56.954
93	15	Naphtha VM&P	09	1.350
15	2	Cobalt Drier	1.671	3.342
1.05	.125	Lead Drier	834	.104
.7	12 fl.	Anti-skinning Agent	0527	.632
	oz.			
34.25	108.91			100.415
	4.35	- 4% Mfg. Loss		
	104.5	Material Cost per Gallon	-	.961
		Direct Labor Cost	-	.042
		Factory Overhead	-	.067
		Bulk Cost per Gallon	-	1.07
		Complete Package Cost	-	.108
		Factory Cost in Package per Gallon	-	1.178