

- 13 -

FORMULAE OF SPECIFIED PAINTS AND VARNISHES
Produced by Three Manufacturers in Chicago, January 1941 - June 1942

MANUFACTURER "A"

Varnish (12-75)

Percentage Formula	Working or Vat Formula
January 1941 to December 1941	January 1941 to December 1941
Percent	Gals. Lbs.
50	Ester Gum 120
12	" 550 Durez Resin 30
19	Dehydrated Castor Oil 10
6	Cooked Oil 13
9	China Wood Oil 2 1/2
4	Flody Soya 5
50	Zinc Acetate 12
	Lead Acetate 6
	Cobalt Acetate 4
	Line
	Oleum 90
50	
100	100

January 1942 to June 1942	January 1942 to May 1942
Percent	Gals. Lbs.
46	Ester Gum 120
36	Dehydrated Castor Oil 28
15	Cooked Oil 10
43	Zinc Acetate 5
6	China Wood Oil 16
100	550 Durez Resin 30
54	Lead Acetate 12
	Cobalt Acetate 6.5
	Oleum 113
100	
100	

June 1942
Gals. Lbs.
"A" Congo Gum 165
" 5 Linseed 9 71.1
Dehydrated Castor Oil 25 202
Zinc Acetate 8
Lead Acetate 10
Cobalt Acetate 4
Solv. Sol. 10 120
Oleum 71 397

Manufacturer stated: "On the percentage formula, we only change this about once because our labels are printed up in large quantities and the minor changes do not change the physical formula a great deal."

OPA 11057

N 4973