

PRODUCT NAME MOLYBDATE CRANGE

NON-BLEEDING

6/22/82

CG 01 CODE YE-698-D PKG

PROCESSES APPROVED BY
YE-698-D (S), F. POST 06/22/82
ALTERNATE
TYPED BY JMH

LOT G2H49

JUL 1 1982

EST. WT. 5527* LBS

MAKING NOTES

JOB NAME: 01YE698DPS

INSTRUCTIONS		PRESSING		RECORD				
VAT			PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	245		STARTED	92				
TIME	7-27		CAKES USED	54				
RELEASED BY	7:46 PM		WATER ON	120				
PRESS	92	93	HRS. WASHED	356				
NO. OF CAKES	54	54	M MHOS					
PRESS WITH AGITATION			HRS. WASHED					
WASH TO 500 M MHOS WITH 35-75% WATER			M MHOS					
TEST AFTER 2 HOURS			HRS. WASHED					
LOAD ON 7 CARS			M MHOS					
			CAKE CONDITION	5+1+1				
			NO CARS LOADED					
			EXPLAIN LOSSES					

SAMPLES 8-02
DELIVER TO CTL.SAMPLED BY MP
RELEASED BY

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLE

NO CARS PULLED

NO DRUMS 20
LUMP WGT 5644

DELIVER

SAMPLED BY
RELEASED BY

CO-GROUND PER CTL INSTRUCTIONS GRINDING

MILL MIKROATOMIZE SCREEN

RPM

SCREEN

RPM

MAX. TEMP DEG F

MAX. TEMP. F

SET ROOF BLAST - GATE AT "9" FOR
HIGH AIR FLOW

EXPLAIN LOSSES

SAMPLE

DATE MIXED

SAMPLES 1 ENV IF GROUND SEPARATELY
DELIVER TO CTLSAMPLED BY
RELEASED BY

N32785

49	E
41	E
17	E
0	T
310	+
12	-
306	+
12	-
315	+
12	-
304	+
12	-
315	+
12	-
323	+
12	-
305	+
12	-
317	+
12	-
293	+
12	-
302	+
12	-
12	-
304	+
12	-
229	+
12	-
3467	T

N32785.01

DUP050464297

49
41
305
0 T

3467 +
322 +
12 -
324 +
12 -
296 +
12 -
185 +
12 -
4546 T

49
41
16
0 T

4546 +
331 +
12 -
354 +
12 -
318 +
12 -
143 +
12 -
5644 T