

VINYL CHLORIDE PRODUCT QUAL REPORT

ETHYL CORPORATION — BATON ROUGE PLANT

CUSTOMER'S
NAME:

9938

Monrovia

CAR NO. 54PX 12760	SALES ORDER NO. 27557	DATE LOADED	DATE SHIPPED 8-31-64
-----------------------	-----------------------	-------------	----------------------

APPEARANCE:

SUSPENDED MATTER NONE; COLOR Colorless; CLARITY Clear

POLYMER

CONVERSION % 97.6

RELATIVE VISCOSITY OF POLYMER

(1% in Cyclohexanone) 2.89

DORELL WEATHERING TEST AT °C @	3.0 ML	0.00
	2.0 ML	0.00
	1.0 ML	0.00
	0.5 ML	0.00

I M P U R I T I E S	ACETYLENE (PPM)	0.0
	ACIDITY (PPM AS HCL)	0.0
	ACETALDEHYDE (PPM)	0.1
	IRON (PPM)	<0.1
	INHIBITOR (PHENOL-PPM)	0
	PEROXIDE (PPM AS H ₂ O ₂)	0.01
	NON-VOLATILE (PPM)	9
	SULFUR (PPM)	0.0
	WATER (PPM)	18

REMARKS

CBY 1112424

ANALYST

Ju Takas