

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE KY-788-P LOT 34818

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
<u>1758</u>	<u>1</u>	<u>6.11</u>	<u>T-34</u>	
<u>1724</u>	<u>1</u>		<u>T-22</u>	

STUMP

TOTAL NET WT. 3482 PKG. N-CODE _____

PROD. SPVR. JW DATE 3/14/80 WHSE. OPER. _____

23
240

03 CODE KY-788-D PKG.
MAR 11 34818
EST. WGT. 950 860 LBS.

TOTES
per C. L. 200

3460

Total Wgt. 3560# Req()

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES KY-788-D (J)	APPROVED BY EMK 9/22/76
	DCG 9/27/76
TYPED BY NE 2/17/77	
MAKING NOTES	

REMARKS

NAME: "KROLOR" YELLOW - LIGHT NON-BLEEDING

INSTRUCTIONS				-PRESSING-	RECORD					
VAT	240				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	3-11-78				STARTED	5:30 PM				
TIME	2:00 P				CAKES USED	46				
RELEASED BY	202 P				WATER ON	9:50 PM				
PRESS	22	23	24		HRS. WASHED	3 1/2				
NO. OF CAKES	46	46	46		OHMS	2000				
PRESS With		AGITATION			HRS. WASHED					
WASH TO 2000		OHMS with 35-75°F water			OHMS					
TEST AFTER	2	HOURS			HRS. WASHED					
LOAD on 6 cars					OHMS					
					CAKE CONDITION					
					NO. CARS LOADED	6				
					EXPLAIN LOSSES					

7DS

SAMPLES 1- 8oz JAR
DELIVER TO Ctl for Color
SAMPLED BY 472 RELEASED BY JLC

-DRYING-

Dry 12 hrs at 220 °F L.V. H.V.
Then Dry 8 hrs at 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

No Drums

SAMPLES
DELIVER TO
NO. CARS PULLED
SAMPLED BY
LUMP WGT. 3424
RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING
SAMPLES 1 Env. & 1 Pt can
DELIVER TO C T L
DATE MIXED
SAMPLED BY
RELEASED BY

34.1
1
32.4
DOT

2.93

-

2.48

-

2.78

-

2.53

-

2.72

-

2.55

-

2.56

-

2.46

-

2.47

-

2.68

-

2.48

-

2.57

-

2.50

-

2.59

-

34.2 T