CG 50 CODE YT-714-D PKG ____ | 35 | YT-714-D (G) EWK 11/19/81

LOT K2H11 SEP 24 1982 | 182 | COMTYP JOB NAME: 50YT714DPG

EST. WT. 2115 * LBS. (20) | MAKING NOTES: _____

INSTRUCTIONS = PRESSING = RECORD

VAT			182		PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE			9-24		STARTED	5AM				
TIME			7		CAKES USED	60				
RELEASED BY			SV		WATER ON	120				
PRESS	32	33	35	36	HRS. WASHED	1 PM				
NO.OF CAKES	60	60	60	60	M MHOS	8½				
PRESS WITHOUT AGITATION					HRS. WASHED	273				
WASH TO 667 M MHOS - 35-75 F WATER					M MHOS					
TEST AFTER 10 HOURS					HRS. WASHED					
LOAD ON 7 CARS					M MHOS					
NOTE WHEN ADVISED BY MAKING SUPVR.:					CAKE CONDITION					
(1) LOAD AS PRESSCAKE IN METAL DRUMS					NO CARS LOADED	1+2+4				
AT 360# NET. DO NOT DRY. TAKE					EXPLAIN LOSSES					
1 QT. SAMPLE.										
(2) HIGH PRESSURE HOSE PRESS & BOX										
AFTER DROPPING THIS BATCH BEFORE										
FALLING NEXT BATCH.					SAMPLED BY					
SUPVR_____ DATE_____					RELEASED BY					
SAMPLES 4 OZ										
DELIVER TO										

= DRYING =

DRY 22 HOURS AT 200 DEG F | LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

NO DRUMS 13

SAMPLES 4 OZ | NO CARS PULLED | LUMP WGT 2250

DELIVER TO | SAMPLED BY

RELEASED BY AK

= GRINDING =

MILL 8 HSP 1/8" RP SCREEN 3700 RPM | SCREEN RPM

MAX. TEMP 140 DEG F | MAX. TEMP. F

IF FOLLOWING ANY DALAMAR CODE OR CPC CODE CLEAN VERY THOUROUGHLY INERT MILL WITH CO2 WHEN GRINDING PER O.P.# O.F.0043 | EXPLAIN LOSSES

SAMPLE WITHOUT MIXING | DATE MIXED

SAMPLES 1 ENV & 1 PT CAN

DELIVER TO CTL | SAMPLED BY

RELEASED BY

200 10-5-82

11
51
231

0.00 *

1.82 +
0.14 -
1.60 +
0.14 -
3.14 *

11
51
16

0.00 *

3.14 +
2.03 +
0.14 -
1.89 +
0.14 -
1.91 +
0.14 -
1.84 +
0.14 -
1.96 +
0.14 -
2.03 +
0.14 -
1.89 +
0.14 -
1.96 +
0.14 -
1.81 +
0.14 -
1.88 +
0.14 -
1.70 +
0.14 -
22.50 *



DUP050103920