

CO 01 CODE YC-16-B PKG. 93

MAY -0-81-E-1227

EST. WGT. 3130 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES (A)	APPROVED BY
YC-16-B	AAC 4-7-75
	JFH 5-5-75
	DCG 5-4-75
TYPED BY	

MAKING NOTES

REMARKS

NAME: MOLYBDATE ORANGE

NON-BLEEDING

INSTRUCTIONS						-PRESSING-		RECORD				
VAT		245				PRESSLOAD		1ST	2ND	3RD	4TH	5TH
DATE		5-7-81				STARTED		9:20				
TIME		9:00 AM				CAKES USED		34				
RELEASED BY		160				WATER ON		1A				
PRESS	91	92	93	2	25	HRS. WASHED		3				
NO. OF CAKES	42	32	32	32	32	OHMS		2000				
PRESS						HRS. WASHED						
WASH TO	2000					OHMS						
TEST AFTER	2					HRS. WASHED						
LOAD ON 4 CARS						OHMS						
						CAKE CONDITION						
						NO. CARS LOADED		5				
						EXPLAIN LOSSES						

SAMPLES

DELIVER TO

SAMPLED BY

RELEASED BY

-DRYING-

DRY	16 HOURS AT	220 F	LUMP: - OK - WET - SALTS - CONTAMINATE
			DRYER SECTIONS USED:
			Color appears dry cannot appear
			for 700 lbs. overnight on heat
			possibly mixed with lot 1228 700 lbs
			ADDITIONAL DRYING HOURS REQUIRED short.
			NO. DRUMS 13
SAMPLES			NO. CARS PULLED
DELIVER TO			SAMPLED BY
			LUMP WGT. 3800
			RELEASED BY RH

-GRINDING-

MICROATOMIZE	SCREEN	RPM
SET ROOF GATE AT 5 INCHES AIR FLOW	MAX. TEMP.	°F
MAGNETIC READING ON ATOMIZER PANEL 1.0"	EXPLAIN LOSSES	
SAMPLE WITHOUT MIXING	DATE MIXED	
SAMPLES 1 ENV		
DELIVER TO C T L	SAMPLED BY	RELEASED BY

1227

41

305

0.00 *

0.00 *

2.81 +.

0.14 ✓

2.96 +.

0.14 ✓

2.87 +.

0.14 ✓

2.89 +.

0.14 ✓

3.10 +.

0.14 ✓

2.88 +.

0.14 ✓

3.01 +.

0.14 ✓

3.09 +.

0.14 ✓

22.49

22.49 +

3.30 +.

0.12 -.

3.48 +.

0.12 -.

3.55 +.

0.12 ✓

3.63 +.

0.12 ✓

2.15 +.

0.12 ✓

38.00 *