PRODUCT NAME = MOLYBDATE ORANGE

CG 01 CODE YE-698-D PKG ____

LOT G2H37 JUN 24 1982

EST. WT. 5527* LBS. 01/R 93 7242

NON-BLEEDING 6/22/82
PROCESSES APPROVED BY
YE-698-D (S) F.POST 06/22/82
ALTERNATE
TYPED BY JMH

MAKING NOTES _____

JOB NAME: 01YE698DPS

- INSTRUCTIONS =					= PRESSING = RECORD					
VAT	24M				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	6-29				STARTED	1935AM				
TIME	10:25Am				CAKES USED	54				
RELEASED BY	DH				WATER ON	5P				
PRESS	2	92	93		HRS. WASHED	8 1/2				
NO.OF CAKES	54	54	54		M MHOS	1135				
PRESS WITH AGITATION					HRS. WASHED					
WASH TO 500 M MHOS WITH 35-75* WATER					M MHOS					
TEST AFTER 2 HOURS					HRS. WASHED					
LOAD ON 7 CARS					M MHOS					
					CAKE CONDITION					
					NO CARS LOADED	8				
					EXPLAIN LOSSES					
SAMPLES 8 OZ					SAMPLED BY					
DELIVER TO CTL.					RELEASED BY	A.K				

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

NO DRUMS 19
LUMP WGT 5762

SAMPLE

NO CARS PULLED
SAMPLED BY
RELEASED BY A.K

DELIVER

Note Finishing Hell Possible metal from Ext Hydraulic in color.

CO-GRIND PER CTL INSTRUCTIONS GRINDING
MILL MIKROATOMIZE SCREEN RPM
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT "9" FOR HIGH AIR FLOW

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE
SAMPLES 1 ENV IF GROUND SEPARATELY
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

N32778



DUP050464278

37
41
348

0.00 *

0.00 *

3.22 +
0.12 -
3.43 +
0.12 -
3.25 +
0.12 -
3.15 +
0.12 -
3.11 +
0.12 -
3.21 +
0.12 -
3.14 +
0.12 -
3.06 +
0.12 -
3.20 +
0.12 -
3.36 +
0.12 -
3.28 +
0.12 -
3.19 +
0.12 -
3.38 +
0.12 -
3.10 +
0.12 -
3.16 +
0.12 -
3.16 +
0.12 -
3.17 +
0.12 -
3.01 +
0.12 -
2.32 +
0.12 -
57.62 *

N32778.01

DUP050464279