Table 3

ASBESTOS EMISSIONS FROM BRAKE LININGS
(Test Results by Electron Micrograph)

	Product	Brand	Test Method	No. of Samples	Conditions of Test-F	Presence of Free Fibers	% Free Fiber
1.	Automobile drum brakes	A	Friction	6	300-800	Few	<1
2.	"	B	Friction	6	250-800	None	0
3.	"	C	Friction	5	300-700	Few	<1
4.	"	C	Friction	1	700-900	Numerous	~10
5.	"	D French	Friction	5	300-800	Few	<1
6.	"	E	Friction	5	300-700	Few	<1
7.	"	F German	Friction	5	300-800	Few	<1
8.	"	G	Friction	2	100-500	Few	<1
9.	"	C	Friction	1	600-700	Numerous	~15
10.	"	H	Friction	2	100-600	Few	<1
11.	Automobile clutch	J	Dynamometer	1	normal driving	None	0
12.	Automobile disk brake	K	Dynamometer	1	normal driving	Few	<5
13.	Bus drum brake	L	Dynamometer	1	city driving	None	0
14.		M	Friction	2	450-550	None	0
15.	Truck drum brake (light)	F	Friction	10	300-800	Few	<1

*Weight estimated from fiber volume.

3-1