MD-3-A

**PACKAGE TICKET** (DRY AND PASTE ONLY)

CODE BT761 LOT 37252

| NET WT/PKG | NO. PKG | PACK. WGT | LOCATION | PO |
|---|---|---|---|---|
| | 12 | 2264 | 3 | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| STUMP | LUMP | 2264 | | |

TOTAL NET WT. 2264 PKG. N–CODE

PROD. SPVR. DATE WHSE. OPER.

12/6/21

N35084




DUP050107577

96/903

CG 32 CODE RT-761-D PKG. ____

→ NOV 19 80 37987

EST. WGT. 2669 LBS.

9 22

PROCESSING INSTRUCTIONS: BATCH UNIT

| PROCESSES | APPROVED BY |
|---|---|
| RT-761-D (J) | JJG 4-4-78 |
| | DCG 4-5-78 |
| TYPED BY | |
| NSA 4-19-78 | |

MAKING NOTES

REMARKS

NAME: WATCHUNG® RED B

NON-BLEEDING

## -PRESSING-

| INSTRUCTIONS | | | | | | RECORD | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|
| VAT | 903 | | | | | PRESSLOAD | 1ST | 2ND | 3RD | 4TH | 5TH |
| DATE | 11/19/80 | | | | | STARTED | 1 Am | | | | |
| TIME | 9:10 Pm | | | | | CAKES USED | 80 | | | | |
| RELEASED BY | P.N. | | | | | WATER ON | 8 | | | | |
| PRESS | 95 | 96 | | | | HRS. WASHED | 5 | | | | |
| NO. OF CAKES | 74 | 80 | | | | OHMS | 35 DD | | | | |
| PRESS without | | AGITATION | | | | HRS. WASHED | | | | | |
| WASH TO 3000 | | OHMS with 35-75°F water | | | | OHMS | | | | | |
| TEST AFTER 3 | | HOURS | | | | HRS. WASHED | | | | | |
| LOAD on 9 cars | | | | | | OHMS | | | | | |
| PRESS IMMEDIATELY CODE | | | | | | CAKE CONDITION | | | | | |
| Instruct making area to add 10# N-588-D half-way thru pressing | | | | | | NO. CARS LOADED | 8 | | | | |
| Clean magnetic separator after pressing | | | | | | EXPLAIN LOSSES | | | | | |
| Cleaned By 375 Time Cleaned 8:29 OK | | | | | | | | | | | |
| SAMPLES | | | | | | | | | | | |
| DELIVER TO | | | | | | SAMPLED BY | | RELEASED BY | | | |

## -DRYING-

| | |
|---|---|
| DRY 20 Hours at 220°F °F | LUMP: - OK - WET - SALTS - CONTAMINATED |
| Hold on track 30 min before dumping pans | No more color in area No Record of any Processing Loss |
| | ADDITIONAL DRYING HOURS REQUIRED |
| | NO. DRUMS 15 |
| SAMPLES | NO. CARS PULLED LUMP WGT. 2269 |
| DELIVER TO | SAMPLED BY RELEASED BY BLL |

## -GRINDING-

| | |
|---|---|
| MILL 2 LSP 1/8" RP SCREEN 1750 RPM | SCREEN RPM |
| MAX. TEMP. 150 °F | MAX. TEMP. °F |
| | EXPLAIN LOSSES |
| SAMPLE / WITHOUT MIXING | DATE MIXED |
| SAMPLES 2 Env & 2 Pt Cans | 227 |
| DELIVER TO C T L | SAMPLED BY RELEASED BY |

DUP050107578

168
12
176
12
184
12
185
12
180
12
179
12
174
12
177
12
178
12
172
12
154
12
39
12
177
12
162
12
144
12
2269

2269

DUP050107579