COPY

Cleveland

Auxiliaries

#30 Coffeyville

December 22, 1960

G.F. Wyman

Lithopone - Light Resistance

12-19-60

I have Vernon's report on the addition of cobalt to our Lithopone to improve the light resistance, which I think it badly needs.

Therefore, I certainly approve of going ahead with the addition of 0.011% as indicated in his Sample "4", unless in the meantime he has found that smaller quantities might be just as advantageous.

(s) S.B.C.

S.B.Coolidge, Jr.:mek

cc: VRH

Cross file The Glidden Co.
Lithopone - Light Resistance



0007-SWP-043218

N23146