CG 03 CODE KY-788-D PKG ____ | KY-788-D (J) FWP 11/05/81

LOT A2H45 24 240 OK

EST. WT. 3489* LBS.

TYPED BY JMH

MAKING NOTES _____

JOB NAME: 03KY788DPJ

INSTRUCTIONS = PRESSING = RECORD

VAT	240				
DATE	15-82	JMH			
TIME	930A				
RELEASED BY					
PRESS	22	23	24	95	96
NO.OF CAKES	46	46	46	40	40

PRESS WITH AGITATION
WASH TO 500 M MHOS WITH 35-75* WATER
TEST AFTER 2 HOURS
LOAD ON 6 CARS

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	9.45AM				
CAKES USED					
WATER ON	46				
HRS. WASHED	12PM				
M MHOS	9				
HRS. WASHED					
M MHOS	460				
HRS. WASHED					
M MHOS					
CAKE CONDITION					
NO CARS LOADED	6				

EXPLAIN LOSSES _____

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY BLL

= DRYING =

DRY 12 HOURS AT 220* F
THEN DRY 8 HOURS AT 160* F

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

NO DRUMS 15
LUMP WGT 346.8

SAMPLES
DELIVER TO

NO CARS PULLED
SAMPLED BY
RELEASED BY BLL

= GRINDING =

MILL 939HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP 150 DEG F

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE W/O MIXING 1 ENV & 2 PT CANS
IF PACKED IN BAGS SAMPLE AS FOLLOWS:
FIRST BAG: 1 ENV.
40TH BAG: 1 ENV. & 2 PINT CANS
LAST BAG: 1 ENV.
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

	5	
	1	
	4	
	0	T
2	2	+
1	4	−
2	7	+
1	4	−
2	0	+
1	4	−
2	2	+
1	4	−
2	5	+
1	4	−
2	0	+
1	4	−
2	9	+
1	4	−
2	2	+
1	4	−
2	5	+
1	4	−
2	6	+
1	4	−
2	0	+
1	4	−
2	8	+
1	4	−
2	5	+
1	4	−
2	1	+
1	4	−
2	5	+
1	4	−
3	7	T

DUP050110216