

Experimental No. CW 769 RAW MATERIAL CHARACTERISTICS AND TESTING Date 10-23-44 No. 1812
Name (Trade) Eustone White Lead Sample Report Card No. 1 Replaces Card No.

Name (Chemical)	Lead Carbonate (Chemically	SIMILAR MATERIALS	
Material (Class)	Pigment /precipitated)	18	
Usage	Chicago Dry Color Dept.	1	
Approximate Price	Date	BW 102	Pulp
Bulk 1.77	Gal./100 lbs. Wt./Gal. 56.64 @ °F.	1031	

ROUTINE TESTS (Must be Run on Each Shipment)					SECONDARY TESTS (Run Different One Each Shipment)				
TEST	Min.	Stan.	Max.	Method	TEST	Min.	Stan.	Max.	Method
Color				421.2	Res 325			0.1%	410
			or	421.1	PbCO ₃			68.6%	706
Strength				422.2	Pb(OH) ₂			30.95%	706
Texture					Lead Acetate			0.15%	717.0
					Moisture			0.30%	407.1
					Total Lead	80%		90%	(704
									(706
					Oil Abs.		9		419.2

N15825

0007-SWP-0048481

SUPPLIER'S NAME	SUPPLIER'S CODE No.
	Euston Std White Lead

Specification: Issued on

Standard Sample Established

Assignment Requested by

REMARKS:

RAW MATERIAL CHARACTERISTICS AND TESTING									
Expt'l No.	CW 769		Sample Report	Card No.	2	Date	5/14/48	No.	1812
Name (Trade)	Eustone White Lead					Replaces Card No.			
Name (Chemical)	Lead Carbonate (Chemically)					SIMILAR MATERIALS			
Material (Class)	Pigment /precipitated)					18			
Usage	Chicago Dry Color Dept.					1			
Approximate Price			Date			% in Tanks	BW 102		
Bulk	1.77	Gal./100 lbs.	Lb./Gal	56.64	%	% in Drums	1031		
ROUTINE TESTS (Must be Run on Each Shipment)					SECONDARY TESTS (Run Different One Each Shipment)				
TEST	Min.	Stan.	Max.	Method	TEST	Min.	Stan.	Max.	Method
VOID - no consumption					VOID Date _____ By _____				
See Card No. 1 for characteristics & remarks.									

N15825.01

0007-SWP-0048483

SUPPLIER'S NAME	SUPPLIER'S CODE No.

Specification: Issued on

Standard Sample Established

Assignment Requested by

REMARKS: