PLAINTIFF'S EXHIBIT

BIR-133

MEMORANDUM

cc: Mr. Hixon - BB
Mr. Frazier - BBR
Mr. Wood - BBR
Mr. Miller - MJ
Mr. Clay - MB
Mr. Clark - PBL

To Mr. Dickinson - PJ

From BBQ

Date October 28, 1977

Subject NO. 15 PERFORATED ASPHALT FELT

On October 26, 1977 I was present when six rolls of #15 perforated asphalt felt, taken from FB stock, were unrolled to check their unrolling characteristics. The results were disappointing as only one of the six could be considered fair, the other five were unsatisfactory. A copy of Forest Clark's report is attached.

Based on this limited inspection it is evident that we still are having difficulty in producing saturated felt at FJ which will unroll freely and be satisfactory to Built-Up roofers.

fed
Attachment

MEMORANDUM

To D. CLAY MB ——→ cc: C. HOMAN BBQ

From F. CLARK PBL

Date 10/27/77

Subject No. 15 PERFORATED ASPHALT FELT

ON 10/26/77, PBL UNROLLED SIX ROLLS OF PERTH AMBOY No. 15 PERFORATED ASPHALT FELT. PRESENT WERE MR. CLAY AND MR. HOMAN.

ONE ROLL WAS SAMPLED FROM EACH OF SIX PALLETS.

ONLY ONE ROLL COULD BE CONSIDERED FAIR. THIS ROLL DECONVOLUTED AND THE LAST THIRTY FEET SHOWED INCREASED RESISTANCE TO UNROLLING. THE SERIAL NUMBER OF THIS ROLL WAS 277A.

THE OTHER FIVE ROLLS DID NOT DECONVOLUTE AND THE LAST HALF OF THE ROLL SHOWED A GREAT RESISTANCE TO UNROLLING. THESE WOULD BE CONSIDERED UNSATISFACTORY. THE SERIAL NUMBERS OF THESE ROLLS WERE 287A AND 287B.

THE CORES OF THESE ROLLS WILL BE SENT VIA HILL TO PERTH AMBOY TO THE ATTENTION OF MR. MILLER.

Cc: 4th 5th

FHC/LA