

INTER-OFFICE MEMO **TENNECO CHEMICALS, INC.**

TO H. B. Carr ✓ AT Burlington DATE August 26, 1969
 FROM E. L. Kanyok AT Burlington COPY TO J. C. Fisher
 SUBJECT Olin-Mathieson Resin A. Stasenko
 File ✓

Quality Control has tested Olin-Mathieson T-510 preshipment sample for conformance to our specifications on 225 type resin.

The results of these tests are as follows:

<u>Properties</u>	<u>T-510</u>	<u>Burlington 225</u>
Relative Viscosity	2.28	2.26 - 2.33
Gels	20	13 maximum
Dry Blend	6.2	6.0 - 8.0
Screen		
+40	-	-
+60	1	0-Tr
+80	3	-
+100	25	40 - 70
+140	79	-
+200	96	-
Thru	4	0-5

E. L. Kanyok
 E. L. Kanyok

ELK/rjl