

**GEORGIA-PACIFIC**

INTERDEPARTMENTAL COMMUNICATION

TO: Mr. J. D. Rauch
FROM: G. W. Green
SUBJECT: TEXTURE FORMULA

DATE: May 20, 1971

LOCATION: Akron

LOCATION: Tigard

PLAINTIFF'S EXHIBIT

GP-2203


Following is the formula for texture referred to in Bill Lehnert's letter of May 20, 1971:

	<u>Lbs/Batch</u>
Limestone	1760
Staramic 330	50
Hamico 267	30
*Cendriv 492S	4
*Paperad	100
*Titanox RA44	50
Nalco	2
*Triton X120	2
Vancide	2
*Pigment BU7052	<u>0.31</u> (5 oz.)

2000.31

*I have made arrangements for enough of each of these to make one ton of the above base. This base is for the coarse and medium textures, formerly known as Bestex C and D. We have tried it in Memphis, with a gypsum base, and it has been very well received there. The small amount of brown pigment is to make the limestone formula match the color of Acme's gypsum formula. Even with the added color, I believe it will still be whiter than your present formula with asbestos.

If you have any questions, please ask.


G. W. G.

GWG:elz

SGP 0006414