MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KY 787 LOT 34556

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
50	64	3200		
	STUMP			

TOTAL NET WT. 3200 PKG. N--CODE 1130

PROD. SPVR.	DATE	WHSE. OPER.
WK	3,4,	

N 26323

DUP050093841

23/240

CG 03 CODE KY-787-D PKG. ____

→ FEB 25 34556

EST. WGT. ~~1090~~ 990 LBS.

OK / KP

Total Wgt. ~~3490#~~ 3390

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-787-D (R)	EWK 9/22/76
Alternate	DCG 9/27/76
TYPED BY	
NE 2/12/77	

MAKING NOTES

REMARKS

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

-PRESSING-

INSTRUCTIONS

VAT	240				
DATE	2/26/80				
TIME	12:01 Pm				
RELEASED BY	PN				
PRESS	22	23	24	24	
NO. OF CAKES	46	46	46	52	

PRESS with AGITATION

WASH TO 2000 OHMS with 35-75°F water

TEST AFTER 2 HOURS

LOAD on 6 cars

BLL

SAMPLES 1-8 oz JAR

DELIVER TO ctl for color

RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	1234				
CAKES USED	46				
WATER ON	6AM				
HRS. WASHED	6				
OHMS	2100				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	6				

EXPLAIN LOSSES

SAMPLED BY 169 RELEASED BY [illegible]

-DRYING-

Dry 12 hrs at 220°F.
Then Dry 8 hrs at 160°F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

No. Drums 15

SAMPLES

DELIVER TO

NO. CARS PULLED

LUMP WGT. 3425

SAMPLED BY

RELEASED BY BLL

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM

MAX. TEMP. 150 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING

SAMPLES 1 ENV & 1 Pt. can

DELIVER TO CTL

DATE MIXED

SAMPLED BY

RELEASED BY

DUP050093842

N 26323.01

34556
41
294

0.00	*
2.45	+
0.14	-
2.58	+
0.14	-
2.63	+
0.14	-
2.57	+
0.14	-
2.50	+
0.14	-
2.47	+
0.14	-
2.49	+
0.14	-
2.43	+
0.14	-
2.50	+
0.14	-
2.46	+
0.14	-
2.49	+
0.14	-
2.54	+
0.14	-
2.53	+
0.14	-
2.54	+
0.14	-
1.17	+
0.14	-
34.25	*

DUP050093843