

Monsanto

ORGANIC CHEMICALS DIVISION

Monsanto Company
800 N. Lindbergh Boulevard
St. Louis, Missouri 63168
Phone: (314) 894-1000

August 14, 1970


Dear Sir:

During the week of August 10, 1970, Monsanto is sending to all its direct customers for Aroclors in plasticizer/modifier application 1) a letter summarizing the latest information on PCBs, and 2) the most recent Aroclor technical bulletin. This bulletin replaces and supercedes O/PL-306 - Aroclor Plasticizers. In as much as some important information concerning recent FDA actions and changes to Monsanto's returned goods policy are discussed, we strongly urge you to forward copies of this bulletin and a letter to your Aroclor customers. Copies of both have been enclosed for your use.

The change in returned goods policy for our direct customers involves a two month extension of the deadlines for returning material to Monsanto. The same two month extension will apply to our distributors. A copy of our revised returned goods policy is attached.

We realize that this additional communication provides an added workload for your people. However, in view of the importance of this matter, we feel it is necessary for you as our distributor to assist in this matter.

Very respectfully,



Walter E. Schalk
Director of Sales
Plasticizers

/dbw

EXHIBIT
WBP M-60

GENERAL POLICY CONCERNING DISTRIBUTORS'
RETURN OF AROCLORS*

1. The following policy will be in effect covering returned goods:
 - a. If unopened containers purchased after September, 1969 are returned to the Sauget, Illinois plant or the Anniston, Alabama plant prior to 10/31/70, 100% of the net purchase price will be allowed for the returned goods. No additional handling charges will be assessed. Freight from distributor's warehouse will be paid by Monsanto at truckload rates.
 - b. If unopened containers purchased after September, 1969 are returned to the Sauget, Illinois plant or the Anniston, Alabama plant prior to 12/31/70, 90% credit will be allowed for the returned goods. No additional handling charges will be assessed. Freight will be paid by the distributor.
 - c. If unopened containers purchased after September, 1969 are returned to the Sauget, Illinois plant or the Anniston, Alabama plant prior to 2/28/71, 50% credit will be allowed for the returned goods. No additional handling charges will be assessed. Freight will be paid by the distributor.
2. Monsanto will accept orders through July 31, 1970 and will make every effort to meet these commitments and to complete shipment as of August 31, 1970. Monsanto reserves the right to limit shipments based on its production capabilities.

*Aroclors 1232, 1242, 1248, 1254, 1260, 1262, 1268,
4465, Montar 1, Toluene/Xylene blends.

Revised 8/14/70

Monsanto

ORGANIC CHEMICALS DIVISION

Monsanto Company
800 N. Lindbergh Boulevard
St. Louis, Missouri 63166
Phone: (314) 884-1000

August 14, 1970

Dear Sir:

You have received our letters of February 27, 1970 and June 1, 1970 covering Monsanto's withdrawal of polychlorinated biphenyls (PCBs) from the market. The February 27 letter reviewed some of the potential hazards of PCBs and of environmental pollution in general. The June 1 letter announced that we were withdrawing all polychlorinated biphenyls used as plasticizers or modifiers from the market, and that the last shipment of these materials would be made August 30, 1970.

In as much as you may have some inventory of these materials which you might be planning to use during the period in which you change over to other products, we felt it imperative to inform you of the latest information concerning PCBs.

It was recently brought to our attention that the Food and Drug Administration has apparently established guidelines setting forth suggested maximum levels of PCBs allowable in certain foods. These levels, as we understand them, are 5 parts per million in fish and 0.2 parts per million in milk. Monsanto, therefore, strongly recommends that PCBs not be used in applications which could lead, either directly or indirectly, to the contamination of food and water supplies for humans or animals. Examples of applications which would seem particularly hazardous would be coatings for water treatment facilities, coatings for food handling equipment, or coatings for such farm items as silos and feed hoppers.

-2-

It has recently come to our attention that PCBs have been found in cows milk. This adds emphasis to Monsanto's recommendation that PCBs not be used in any application where they might come in contact with or otherwise contaminate food, silage, water supplies, etc.

The latest available bulletin on our line of Aroclors is enclosed for your use. This publication replaces and supercedes bulletin O/PL-306 - Aroclor Plasticizers. The only products listed which will be sold after August 31, 1970 are 1) Aroclor 1221, a monochlorinated biphenyl which is readily biodegradable, and 2) Aroclors 5442 and 5460, both chlorinated terphenyls which have not shown themselves to be environmental contaminants. Please pay special attention to the section of this bulletin which relates to environmental hazards.

In addition to the products listed above which will remain on the market, Monsanto will sell a series of blends of Aroclor 1221 and Aroclor 5460 which will replace the polychlorinated biphenyls for many applications.

During this withdrawal of PCBs from the market, Monsanto has had in effect a modified returned goods policy stating that unopened containers less than one year old could be returned for full credit through July 31, 1970. From August 1 through August 31, 1970, 90 percent credit would be allowed. From September 1 through December 31, 1970, 50 percent credit would be allowed. The customer will pay all return freight. All of the dates in the time schedule for this returned goods policy are hereby extended an additional two months.

Monsanto realizes that the removal of these products from the market has caused a great deal of concern and expense for our customers. This is certainly regrettable. However, it appears to us that as a responsible supplier, this is the only reasonable course of action. We stand ready to assist you as we can with your reformulation work.

Very respectfully,

Walter E. Schalk
Walter E. Schalk
Director of Sales
Plasticizers

/abw

T E C H N I C A L B U L L E T I N

AROCLOR® PLASTICIZERS

A series of inert, chemically-resistant, fire-retarding plasticizers compatible with wide variety of resins.

TECHNICAL BULLETIN O/PL-306A

Monsanto

AROCOR® PLASTICIZERS

A series of inert, chemically-resistant, fire-retarding plasticizers compatible with wide variety of resins.

TECHNICAL BULLETIN O/PL-308A

CAUTION: see sections entitled Toxicity and Safe Handling, and Environmental Hazards, on page 12.

"Nothing contained herein is to be construed as a recommendation to use any product in conflict with any patent. MONSANTO MAKES NO WARRANTIES AS TO THE FITNESS OR MERCHANTABILITY OF ANY PRODUCTS REFERRED TO, or guarantee of satisfactory results from reliance upon contained information or recommendations, and disclaims all liabilities for any resulting loss or damage."

Organic Chemicals Division/800 N. Lindbergh Blvd./St. Louis, Missouri 63165

Introduction

The unique Aroclor® plasticizers are among the most versatile chemically produced materials available. One outstanding characteristic — *inertness* — makes Aroclor useful in many ways for many different applications. The major benefits offered by Aroclor include:

- Chemical Resistance
- Fire Retardance
- Compatibility with most resins
- Nonoxidation
- Adhesivity
- Low Cost

Monsanto's Aroclor plasticizers comprise a series of chlorinated biphenyls and chlorinated polyphenyls. They vary from mobile, oily liquids to white crystals and hard, transparent resins.

Twelve of the Aroclor plasticizers, each of which represents a series, are discussed in this bulletin. An understanding of the system for designation of each Aroclor should prove useful in the evaluation of the property gradations among them. The last two digits indicate the approximate weight percentage of chlorine in the product, and the first two digits indicate the type of material, as follows:

- 12 — chlorinated biphenyls
- 25 — blend of chlorinated biphenyls and chlorinated triphenyls (75:25)
- 44 — blend of chlorinated biphenyls and chlorinated triphenyls (60:40)
- 54 — chlorinated triphenyls

For nearly every Aroclor mentioned, a darker, less-pure grade exists, with about the same physical and chemical characteristics, but lower in price.

Solubility

The Aroclor liquids and resins are readily soluble in most common organic solvents and drying oils. Although all Aroclor plasticizers are insoluble in water, the hard, crystalline materials are generally less soluble than the liquids and softer resins. Solubilities of some Aroclor plasticizers are shown in Table 1.

TABLE 1

SOLUBILITIES OF ARACLO® PLASTICIZERS IN VARIOUS SOLVENTS											
Solvent	Araclo 1242		Araclo 1244		Araclo 1254		Araclo 1266		Araclo 4465		Araclo E469
	25°C	Hot	25°C	Hot	25°C	Hot	Cold	Hot	Cold	Hot	25°C
Acid											
Acetic Acid	S	S	—	—	S	S	—	—	SS	S	—
Oleic Acid	S	S	—	—	S	S	—	—	S	VS	—
Benzic Acid	10.0 ^{25°C}	—	10.0 ^{25°C}	—	—	—	—	—	—	—	—
Aldehyde											
40% Formaldehyde	I	I	I	I	I	I	I	I	I	I	—
Formal	VS	VS	VS	VS	VS	VS	SS	SS	VS	VS	—
Amine											
Aniline	S	S	—	—	S	S	—	—	VS	VS	—
Pyridine	132.5 ^{25°C}	440 ^{25°C}	—	—	114 ^{25°C}	425 ^{25°C}	—	—	VS	VS	—
Chloro derivatives											
Amyl chlorides — mixed	S	S	S	S	S	S	—	—	VS	VS	—
Carbon Tetrachloride	S	S	S	S	S	S	—	—	VS	VS	156
Chloroform	S	S	S	S	S	S	S	S	VS	VS	—
Dichloroethylene	—	—	—	—	—	—	—	—	VS	VS	—
Ethylene Dichloride	S	S	S	S	S	S	S	S	VS	VS	—
Monochlorobenzene	S	S	S	S	S	S	—	—	VS	VS	—
Orthodichlorobenzene	—	—	—	—	—	—	—	—	VS	VS	—
Tetrachloroethane	S	S	S	S	S	S	—	—	VS	VS	—
Trichloroethane	S	S	S	S	S	S	—	—	VS	VS	—
Trichloroethylene	S	S	S	S	S	S	—	—	VS	VS	—
Drying Oil											
Tung Oil	S	S	S	S	S	S	—	—	VS	VS	—
Unseed Oil	S	S	S	S	S	S	I	S	VS	VS	—
Ester											
Amyl Acetate	S	S	S	S	S	S	S	S	VS	VS	—
Butyl Acetate	S	S	S	S	S	S	S	S	VS	VS	—
"Calozole" Acetate	S	S	S	S	S	S	—	—	VS	VS	—
Cottonseed Oil	S	S	S	S	S	S	—	—	S	VS	—
Dibutyl Phthalate	S	S	S	S	S	S	S	S	S	VS	—

Diethyl Phthalate	S	S	S	S	S	S	—	—	S	VS	—
Ethyl Acetate	S	S	S	S	S	S	SS	SS	S	VS	—
Ethyl Lactate	S	S	S	S	S	S	—	—	VS	VS	—
Ethylene Glycol Diacetate	S	S	S	S	S	S	—	—	VS	VS	—
Methyl Acetate	S	S	S	S	S	S	SS	SS	S	S	—
Triethyl Phosphate	S	S	S	S	S	S	—	—	SS	S	—
Ether: Ethyl Ether	S	S	S	S	S	S	S	S	S	—	—
Ether Alcohol											
<i>Ceritol</i> [*]	224 ¹⁰ °C	307 ¹⁰ °C	VS	VS	172 ²⁵ °C	259 ¹⁰ °C	—	—	S	SS	—
Cellulosolve	S	S	S	S	S	S	—	—	S	—	—
Diethylene Glycol	—	—	—	—	—	—	—	—	S	—	—
<i>p,p'</i> -Dihydroxy Ethyl Ether	16.0 ²³ °C	19 ¹⁰ °C	SS	SS	83 ¹⁰ °C	100 ¹⁰ °C	—	—	SS	—	—
Hydrocarbon											
Benzene	VS	VS	VS	VS	VS	VS	S	S	VS	VS	143
Gasoline	VS	VS	VS	VS	VS	VS	—	—	VS	VS	—
Kerosene	VS	VS	VS	VS	VS	VS	SS	S	VS	VS	—
Mineral Spirits	VS	VS	VS	VS	VS	VS	S	S	VS	VS	—
Paraffin	2.0 ²³ °C	S	2.0 ¹⁰ °C	S	—	S	—	—	S.S	S	—
Pine Oil	S	S	VS	VS	S	S	S	S	S	S	—
Toluene	VS	VS	VS	VS	VS	VS	S	S	VS	VS	142
Turpentine	VS	VS	VS	VS	VS	VS	S	S	VS	VS	—
Xylene	VS	VS	VS	VS	VS	VS	S	S	VS	VS	178
Hydroxy derivatives											
Amyl Alcohol	S	S	—	—	S	S	SS	S	S	S	—
<i>n</i> -Butyl Alcohol	S	S	—	—	S	S	—	SS	SS	S	—
Ethyl Alcohol (3-A)	21.3 ¹⁰ °C	80.0 ¹⁰ °C	—	—	18 ¹⁰ °C	28 ¹⁰ °C	—	—	SS	—	—
Glycerine	—	—	—	—	—	—	—	—	—	—	—
Methyl Alcohol	42.5 ¹⁰ °C	88.5 ¹⁰ °C	—	—	15 ¹⁰ °C	22.2 ¹⁰ °C	—	—	SS	—	—
Phenol — 90%	194 ¹⁰ °C	S	—	—	SS	S	SS	S	S	S	—
Ketone: Acetone	S	S	—	—	S	S	—	—	S	S	250
Miscellaneous											
Carbon Disulfide	S	S	—	—	S	S	S	S	VS	VS	—
Nitrobenzene	S	S	—	—	S	S	—	—	VS	—	—
Water	—	—	—	—	—	—	—	—	—	—	—

I — Insoluble SS — Slightly Soluble S — Soluble VS — Very Soluble.
 Figures show grams of Aroclor per 100 milliliters of solvent at 25°C unless otherwise indicated.
^{*}Trademark of Union Carbide Corp.

TABLE 2

CHEMICAL AND PHYSICAL PROPERTIES OF REPRESENTATIVE AROCLOR® PLASTICIZERS AND RESINS

Property	Aroclor 1221	Aroclor 1232	Aroclor 1242	Aroclor 1248	Aroclor 1254
Appearance	Clear, mobile oil	Clear, mobile oil	Clear, mobile oil	Clear, mobile oil	Light-yellow viscous liquid
Color, maximum	*100 APHA	*100 APHA	*100 APHA	*100 APHA	*100 APHA
Chlorine, percent	20.5-21.5	31.5-32.5	42	48	54
Acidity, mg KOH/g, maximum	*0.014	*0.014	*0.015	*0.010	*0.010
Moisture, ppm, maximum	—	—	*50	*50	*50
Ave. Coefficient of Expansion, cc/cc/°C	0.00071 (15°-40°C)	0.00073 (25°-100°C)	0.00068 (25°-65°C)	0.00070 (25°-65°C)	0.00066 (25°-65°C)
Specific Gravity	*1.182-1.192 (25°/15.5°C)	*1.270-1.280 (25°/15.5°C)	*1.381-1.392 (25°/15.5°C)	*1.405-1.415 (65°/15.5°C)	*1.495-1.505 (65°/15.5°C)
Density, pounds per gallon, 25°C	9.85	10.55	11.50	12.04	12.62
Distillation Range, °C, extracted (ASTM D-20, modified)	275-320	290-325	325-366	340-375	365-390
Evaporation Loss, %, 100°C, 6 hours (ASTM D-6, mod.) 163°C, 6 hours	1.0-1.5	1.0-1.5	0-0.4 3.0-3.6	0-0.3 3.0-4.0	0-0.2 1.7-1.3
Flash Point (Cleveland Open Cup), °C °F	141-150 286-302	152-154 305-310	176-180 348-356	193-198 373-384	None to boiling point
Fire Point (Cleveland Open Cup), °C °F	176 349	238 460	None to boiling point	None to boiling point	None to boiling point
Pour Point (ASTM E-97), °C °F	1 (crystals) 34 (crystals)	-35.5 -32	-19 2	-7 19.4	10 50
Softening Point (ASTM E-28), °C °F	—	—	—	—	—
Refractive Index, n D-20 20°C	1.617-1.618	1.620-1.622	1.627-1.628	1.630-1.631	1.639-1.641
Viscosity, Seconds Saybolt Universal (ASTM D-88) 100°F (37.8°C) 130°F (54.4°C) 210°F (98.9°C)	*38-41 35-37 30-31	*44-51 39-41 31-32	*82-92 49-56 34-35	185-240 *73-80 30-37	1800-2500 260-340 *44-46

*Minimum Specification.

Aroclor 1280	Aroclor 1262	Aroclor 5442	Aroclor 4465	Aroclor 2655	Aroclor 5450	Aroclor 1268
Light-yellow, soft, sticky resin	Light-yellow sticky, viscous resin	Clear yellow sticky resin	Clear, light-yellow, resin	Black, opaque, brittle resin	Clear, yellow- to-amber, brittle resin or flakes	White to off-white powder
*150 APHA	*150 APHA	*2 NPA (molten)	*2 NPA (molten)	—	*2 NPA (molten)	*1.5 NPA (molten)
60	61.5-62.5	42	66	65	59.5-60.5	83
*0.014	*0.014	0.05	0.05	1.4	0.05	0.05
*50	—	—	—	—	—	—
0.00067 (20°-100°C)	0.00064 (25°-65°C)	0.00123 (25°-69°C)	0.00081 (25°-65°C)	0.00056 (25°-65°C)	0.00179 (25°-124°C)	0.00067 (20°-100°C)
*1.555-1.568 (90°/15.5°C)	*1.572-1.583 (90°/15.5°C)	1.470 (25°/25°C)	1.670 (25°/25°C)	1.734 (25°/25°C)	1.670 (25°/25°C)	1.804-1.811 (25°/25°C)
13.50	13.72	12.24	13.91	14.44	13.91	15.09
385-420	390-425	215-300 (4 mm. Hg)	230-320 (4 mm. Hg)	—	280-335 (5 mm. Hg)	435-450
0-0.1 0.5-0.8	0-0.1 0.5-0.8	0.01 0.2	0-0.02 0.2-0.3	0.2-0.3	0.03	0-0.06 0.1-0.2
None to boiling point	None to boiling point	247 477	None to boiling point	—	None to boiling point	None to boiling point
None to boiling point	None to boiling point	> 360 > 662	None to boiling point	—	None to boiling point	None to boiling point
31 88	38-38 89	48 115	—	—	—	—
—	—	*48-52 115-125	*60-68 140-151	*66-72 149-162	*98-105 208-222	*150-170 (hold 302-338 point)
1.647-1.649	1.6501-1.6517	—	1.664-1.667	—	1.660-1.665	—
3200-4500 *72-78	600-950 (160°F; 71°C) *86-100	380-400	90-150 (266°F; 130°C)	—	—	—

*Monomer Spec. (Molten).

Density

All the Aroclor plasticizers are heavier than water, a valuable property for many applications. Densities are shown in Figure 1.




Fig. 1 — Densities of Aroclor® Plasticizers at Various Temperatures

Specific Volume

The specific volume of Aroclor 1248 at different temperatures is as follows:

Temperature (°F)	Aroclor® 1248 Specific Volume (ml/g)
0	0.674
100	0.699
200	0.726
300	0.755
400	0.790
500	0.828
600	0.870

The low vaporization loss of Aroclor plasticizers is indicated in Table 3.

TABLE 3

VAPORIZATION RATES OF AROCLOR® PLASTICIZERS

<i>Plasticizer</i> (Surface area: 12.28 sq. cm.)	<i>Wt. Loss</i> (g)	<i>Exposure</i> at 100°C (hr.)	<i>Vaporization</i> Rate (g/sq. cm./hr.)
Aroclor 1221	0.5125	24	0.00174
Aroclor 1232	0.2572	24	0.000874
Aroclor 1242	0.0995	24	0.000338
Aroclor 1248	0.0448	24	0.000152
Chloris® -42-S	0.0745	48	0.000126
Dioctyl phthalate	0.0686	48	0.000117
Dutrex® 25	0.0256	24	0.000087
Aroclor 1254	0.0156	24	0.000053
Shell Dutrex 20	0.0047	24	0.000016
Aroclor 1262	0.0039	24	0.000013
Aroclor 1260	0.0026	24	0.000009
Aroclor 4465	0.0064	72	0.000007
Aroclor 5442	0.0039	72	0.000004
Aroclor 5460	0.0032	72	0.000004
Tricresyl phosphate	0.0010	24	0.000003

It is concluded that the vaporization rates of Aroclor plasticizers — especially the most widely used 1254 and 1260 — compare most favorably with the similar constants of other plasticizers selected specifically for these tests because of their low vaporization rates.

*Trademark of Hercules, Inc.

**Trademark of Shell Oil Co.

Vapor Pressure

The vapor pressures of several Aroclor plasticizers are indicated in Figure 2 over the temperature range 150° to 300°C.




Fig. 2 — Vapor Pressures of Aroclor® Plasticizers

The estimated vapor pressures of several Aroclor plasticizers at 100°F shown in the following table were determined by extrapolation from the values shown in Figure 2.

Approximate Vapor Pressure of Aroclor® Plasticizers
Estimated at 100° F (37.8° C)

Aroclor 1232	0.005 mm. Hg
Aroclor 1242	0.001 mm. Hg
Aroclor 1248	0.00037 mm. Hg
Aroclor 1254	0.00006 mm. Hg

Viscosity

The viscosities of the Aroclor plasticizers vary according to whether the base material is a biphenyl or a polyphenyl and on the degree of chlorination. In general the low-chlorinated biphenyls have the lowest viscosities (Figure 3).




Fig. 3 — Viscosity Ranges of Some Aroclor® Plasticizers

Toxicity And Safe Handling

Inhalation

At ordinary temperatures the Aroclor chlorinated polyphenyls have not presented industrial toxicological problems. The hazard of potential toxic exposure varies with their volatility: the lower-chlorinated, more-volatile ones present more of a potential problem from the standpoint of both inhalation and skin contact. When Aroclor plasticizers are used at elevated temperatures, engineering controls must be applied, either by the use of closed systems or by effective local-exhaust ventilation together with general workroom exhaust.

Vapor of the liquid Aroclor plasticizers at room temperature should not be breathed in a confined space, and no vapor of any Aroclor evolved at elevated temperatures should be allowed to be dispersed into the general workroom.

Inhalation tests on animals indicate that the maximum safe concentration of vapor is in the range of from 0.5 to 1.0 milligram of the lower-chlorinated Aroclor plasticizers per cubic meter of air. The threshold limit values (maximum allowable concentration for an 8-hour working day) set by the American Conference of Government Hygienists are 1.0 milligram of the lower-chlorinated Aroclor compounds per cubic meter of air and 0.5 milligram of the more-highly-chlorinated compounds, such as Aroclor 1254, per cubic meter of air.

Skin Contact

Schwartz patch tests on 200 volunteers showed that Aroclor 1254 was neither a primary skin irritant or a sensitizer.

Prolonged or repeated skin contact with the Aroclor plasticizers must be avoided by the use of gloves and protective garments, because of the possible occurrence of a condition called chloracne. Although reports of this condition caused by Aroclor are rare, it can be produced by excessive skin contact. If any Aroclor is spilled on the skin the skin should be washed in the usual manner with a soap solution.

A burn caused by contact with a hot Aroclor should be treated like any ordinary burn. Aroclor plasticizer adhering to the burned area need not be removed immediately, unless treatment of the burn demands it, in which case either soap and water or repeated washings with a vegetable oil are recommended.

Environmental Hazards

Aroclor 1232, Aroclor 1242, Aroclor 1248, Aroclor 1254, Aroclor 1260, Aroclor 1262, Aroclor 1268, Aroclor 4465, and Montar 1 all contain polychlorinated biphenyls (PCB) of various types and in varying amounts. PCB residues in small amounts have been found in the environment and some studies have indicated that they may be harmful to certain forms of animal life. Extreme care should therefore be taken by all users of PCB-containing products to prevent any entry into the environment through spills, leakage, use, disposal, vaporization or otherwise. Further, the products in which PCB materials are used, or which are formulated using PCB materials as a component, should be given careful study to eliminate the possibility that PCB might reach the environment as a result of use in a given application.

Some specific applications where the use of PCB should definitely be avoided are in paints and sealants for swimming pools, paints and waterproofing agents in silos and other buildings where food products for humans or animals are stored, and as a component of any container or wrapping used in the packaging of food products.

Shipping

Freight Classification

Aroclor 1221, 1232, 1242, 1248, 1254, 1260, 1262	Synthetic Resin, Liquid, NOIBN
---	--------------------------------

Rail Classification

Aroclor 1268, 4465, 5442, 5460	Synthetic Resin, Other Than Liquid, NOIBN
-----------------------------------	--

Truck Classification

Aroclor 1268	Synthetic Resin, Powder, NOI
Aroclor 4465, 5442, 5460	Synthetic Resin, Lumps or Solid Mass, NOI

Shipping Regulations

None

Standard Containers

Aroclor 1221	Tank car, 520-lb. steel drum, 50-lb. can
Aroclor 1232	Tank car, 550-lb. steel drum, 50-lb. can
Aroclor 1242, 1248, 1254, 1260, 1262	Tank car, 600-lb. steel drum, 50-lb. can
Aroclor 1268	200-lb. fiber drum, 25-lb. fiber drum
Aroclor 4465	500-lb. steel drum, 50-lb. can
Aroclor 5442	450-lb. steel drum, 50-lb. can
Aroclor 5460 (flaked)	50-lb. bag

DISTRICT SALES OFFICES ALL DIVISIONS

AKRON, OHIO 44313

260 Springside Drive
Montrose Development Park
Tel. (216) 666-4111

ATLANTA, GEORGIA 30326

Lenox Towers East
3400 Peachtree Rd. N. E. - Suite 1711
Tel. (404) 577-2260

BOSTON, MASSACHUSETTS 02149

Everett Station
Tel. (617) 387-6010

CHICAGO, ILLINOIS

3158 Des Plaines Ave.
Des Plaines, Illinois 60018
Tel. (312) 296-6688

CINCINNATI, OHIO 45206

1501 Madison Road
Tel. (513) 761-6707

DETROIT, MICHIGAN

500 Northland Towers West
Southfield, Mich. 48075
Tel. (313) 357-0910

HONOLULU, HAWAII 96812

205 Pacific International Bldg.
677 Ala Moana Blvd., P. O. Box 3824
Tel. (808) 531-2744

HOUSTON, TEXAS 77027

1301 Post Oak Tower
6051 Westheimer Road
Tel. (713) 621-9550

LOS ANGELES, CALIFORNIA 90022

6670 E. Flamingo St.
Tel. (213) 723-2492

NEW YORK, NEW YORK 10017

277 Park Avenue
Tel. (212) 922-4111

ST. LOUIS, MISSOURI 63166

800 N. Lindbergh Blvd.
Tel. (314) 694-1000

SAN FRANCISCO BAY AREA

2710 Lafayette, Santa Clara, Calif. 95052
Tel. (408) 243-0414

SEATTLE, WASHINGTON 98121

2112 Third Avenue
Tel. (206) 622-4203

WILMINGTON, DELAWARE 19803

2005 Concord Pike, Falken
Tel. (302) 658-6531

MONSANTO, 800 N. LINDBERGH BLVD., ST. LOUIS, MISSOURI 63166

Additional District Offices
are maintained by:

Agricultural Division

ALLENTOWN, PENNSYLVANIA 18104
Park Professional Building
2200 Hamilton Street
Tel. (215) 437-8471

DECATUR, ILLINOIS 62523
207 Decatur Professional Building
363 South Main Street
Tel. (217) 423-8031

DES MOINES, IOWA 50310
312 Maple Hay Tower
Tel. (515) 276-8503

FREMONT, NEBRASKA 68026
150 South Main Street
Tel. (402) 727-1230

INDIANAPOLIS, INDIANA 46206
Suite 215, 4002 Meadows Drive Building
Tel. (317) 847-9146

KANSAS CITY, MISSOURI 64133
701 Blue Ridge Tower
4240 Blue Ridge Boulevard
Tel. (816) 363-8060

LULING, LOUISIANA 70070
P. O. Box 174
Tel. (504) 784-6283

MANKATO, MINNESOTA 56001
111 Madison East
Tel. (507) 387-3408

MEMPHIS, TENNESSEE 38104
303 Union Plaza Building
1836 Union Avenue
Tel. (901) 276-7811

MUSCATINE, IOWA 52761
P. O. Box 473
Tel. (319) 263-1331

Hydrocarbons & Polymers Division

NEW ENGLAND AREA
730 Worcester St.
Indian Orchard, Mass. 01061
Tel. (413) 788-6911

Lion Oil
EL DORADO, ARKANSAS 71710
Lion Oil Building
Tel. (501) 883-3111

JACKSON, MISSISSIPPI 39208
P. O. Box 10837, Westland Station
Tel. (601) 362-3648

N. LITTLE ROCK, ARKANSAS 72110
410 West 8th Street, P. O. Box 6821
Tel. (501) 376-2437

MEMPHIS, TENNESSEE 38113
1022 Riverside Drive, P. O. Box 13248
Tel. (901) 848-4451

Plastic Products & Resins Division
EUGENE, OREGON 97402
855 Serene Road
Tel. (503) 342-7201

KENILWORTH, NEW JERSEY 07033
North Seventh St. & Monroe Ave.
Tel. (201) 276-2900

SPRINGFIELD, MASS. 01101
P. O. Box 2130
Tel. (413) 788-8911

Textiles Division

ATLANTA, GEORGIA 30303
Atlanta Merchandise Mart
240 Peachtree St. N. W.
Tel. (404) 577-2260

CHARLOTTE, NORTH CAROLINA 28210
6230 Fairview Road, Suite 400
Tel. (704) 364-0110

GREENVILLE, SOUTH CAROLINA 29606
McAllister Plaza
P. O. Box 5584, Station B
Tel. (803) 239-9171

NEW YORK, NEW YORK 10001
350 Fifth Ave.
Tel. (212) 666-6100

3/70

Monsanto 800 N. LINDBERGH BLVD., ST. LOUIS, MISSOURI 63166

Monsanto

FROM: NAME & LOCATION:

P. W. Gann - B2SF

DATE

May 9, 1973

SUBJECT

PCB Warning Letter, August 14, 1970
By Schalk

REFERENCE

TO

Memo to File

This warning letter was sent to the following four distributors:


E. M. Toby, President
American Mineral Spirits Co.
Division of Union Oil of California
1345 Avenue of the Americas
New York, New York 10019

Mr. Carl Giloth
Central Solvents & Chemical Co.
2540 West Fluornoy Street
Chicago, Illinois 60612

Mr. W. C. McCall, President
Great Western Chemical Co.
3720 North West Yeon Ave.
Portland, Oregon 97210

Mr. G. J. Turriff, President
Tab Chemical Co.
4801 South Austin
Chicago, Illinois 60638

This is the same list as used in May 25, 1970 letter.


P. W. Gann

/mc

EXHIBIT
WBP-M-601

W. REV. 1-72

DISTRIBUTORS

A list of our distributors and their regional offices is attached. The letter that was sent to the head offices of the distributors on 5/25/70 is enclosed.

EXHIBIT
WBP M 60 2

AMERICAN MINERAL SPIRITS COMPANY

Baltimore, Maryland

Charlotte, North Carolina

Conshohocken (Philadelphia), Pennsylvania

Miami, Florida

Palatine (Chicago), Illinois

Plainfield, New Jersey

Providence, Rhode Island

Tucker (Atlanta), Georgia

CENTRAL SOLVENTS & CHEMICALS COMPANY

Allegheny Solvents & Chemical	Pittsburgh, Pennsylvania
Amsco Solvents & Chemical	Cincinnati, Ohio
Buffalo Solvents & Chemical	Buffalo, New York
Central Solvents & Chemical	Santa Fe Springs, California
Central Solvents & Chemical	San Francisco, California
Central Solvents & Chemical	Portland, Oregon
Central Solvents & Chemical	Kent, Washington
Dixie Solvents & Chemical	Louisville, Kentucky
Hoosier Solvents & Chemical	Indianapolis, Indiana
Missouri Solvents & Chemical	St. Louis, Missouri
Missouri Solvents & Chemical	Kansas City, Missouri
Ohio Solvents & Chemical	Cleveland, Ohio
Texas Solvents & Chemical	Dallas, Texas
Texas Solvents & Chemical	Houston, Texas
Toledo Solvents & Chemical	Toledo, Ohio
Western Eaton Solvents	Detroit, Michigan
Wisconsin Solvents & Chemical	Milwaukee, Wisconsin
Wolverine Solvents & Chemical	Grand Rapids, Michigan
Southern Solvents & Chemical	New Orleans, Louisiana

GREAT WESTERN CHEMICAL COMPANY

Portland, Oregon

Richmond, California

Seattle, Washington