

CONFIDENTIAL

FOR INTERNAL USE ONLY

DISTRIBUTION: R. Mack
R. Dirksen
J. Kozdron
M. Collins
K. Patel
R. Smith (3)
J. Latsko

ROUTE: HC, TCK, RR,
MS, JS, JKS

AIRFLEX TEST REPORT

TITLE CS-CT FRICTION MATERIAL (SCAN-PAC)

PROJECT NUMBER Z0952-4 TEST DATES 11/78

PROJECT ENGINEER J. Latsko & T. Mowry TEST STAND FMTM

TECHNICIAN (S) J. Denk

APPROVED BY Roger L. Smith REPORT DATE November 9, 1979

1.0 ABSTRACT

Three non-asbestos types of friction materials were tested and compared to previous data for CS-CT friction material (Fenner 333 friction material). Two of the materials had higher overall coefficients of friction than the Fenner material, but, due to the "hard cured" rigidity of the two linings, cracking of the material in an actual brake application could be a problem and would have to be tested. It is recommended that further screening of additional materials be pursued before actual brake testing.