

BCC: R. M. Hutchis
J. Walker, Franklin
S. Meyer, Long Beach
C. Stelchek, Dennison
G. DeLong, Green Cove Springs
A. C. Daley, DEQ
J. E. Swensen, Attention: A. Corsano
C

File 20-1-6-1

March 20, 1967

Mr. T. S. Gable
National Sanitation Foundation Testing Laboratory, Inc.
2355 W. Stadium Blvd.
P. O. Box 1468
Ann Arbor, Michigan

Dear Tom:

In your letter of March 10, 1967 to A. V. Humphrys you indicate that there is a discrepancy between what we consider to be NSF approved formulas and what you have listed as approved formulas.

Our records (My letter of August 24, 1966 to C. A. Parish, his letter of August 31, 1966 to me, my letter of December 20, 1966 and your letter of January 19, 1967.) show that you have approved for use by J-M the following formulas: 26, 26A, 26-2, 26A-2, 26A-4, 26B-3, 26A, and 26A-9. Your letter of January 19, 1967 refers to 26-A, but I am sure this was meant to be 26A-9.

We have another formula which has been approved by the FPI (notification may not have reached you yet) that we would like to add to the list. This is 26-9, identical to 26A-9 except that a different resin and stabilizer is used with a minor adjustment of the lubrication.

Please note that, although J-M has a number of formulas now (and this will increase in the future), they are basically all the same from the toxicological and organoleptic point of view. They must be considered different formulas to conform to the FPI rules.

If some of the correspondence we refer to is not in your file, please let us know and we will furnish copies. For your convenience, I have attached a composite of the list we consider approved by you plus 26-9. If this letter does not clear up the confusion, please let me know, Tom. We would also appreciate your concurrence on our use of 26-9.

Very truly yours,

R. T. Hucks

RTH:eb
Attachment
cc: A. V. Humphrys, DEQ

J-M 83

MTC 010649

BCC: R. M. Hutchis
J. Walker, Franklin
S. Moyer, Long Beach
C. Stelchek, Denison
G. DeLong, Green Cove Springs
A. C. Daley, DHQ
J. H. Swensen, Attention: A. Corsano
C

File 20-1-6-1

March 20, 1967

Mr. T. S. Gable
National Sanitation Foundation Testing Laboratory, Inc.
2355 W. Stadium Blvd.
P. O. Box 1468
Ann Arbor, Michigan

Dear Tom:

In your letter of March 10, 1967 to A. V. Humphrys you indicate that there is a discrepancy between what we consider to be not approved formulae and what you have listed as approved formulae.

Our records (My letter of August 24, 1966 to C. A. Parish, his letter of August 31, 1966 to me, my letter of December 20, 1966 and your letter of January 19, 1967.) show that you have approved for use by J-M the following formulae: 26, 26A, 26-2, 26A-2, 26A-4, 26B-3, 26A, and 26A-9. Your letter of January 19, 1967 refers to 26-A, but I am sure this was meant to be 26A-9.

We have another formula which has been approved by the PFI (notification may not have reached you yet) that we would like to add to the list. This is 26-9, identical to 26A-9 except that a different resin and stabilizer is used with a minor adjustment of the lubrication.

Please note that, although J-M has a number of formulae now (and this will increase in the future), they are basically all the same from the toxicological and organoleptic point of view. They must be considered different formulae to conform to the PFI rules.

If some of the correspondence we refer to is not in your file, please let us know and we will furnish copies. For your convenience, I have attached a composite of the list we consider approved by you plus 26-9. If this letter does not clear up the confusion, please let me know, Tom. We would also appreciate your concurrence in our use of 26-9.

Very truly yours,

R. T. Hucks

RTH:eb
Attachment
cc: A. V. Humphrys, DHQ

MTC 010650

52

s&f Formulae - March 15, 1967

Material	26	26-2	26-A	26A-2	26A-4	26A-9	26B-1	29A	26-9
Resin									
PVC 450	---	---	100.0	100.0	100.0	100.0	---	100.0	---
Geon 103 EP	100.0	100.0	---	---	---	---	---	---	100.0
Cumberland 220	---	---	---	---	---	---	100.0	---	---
Stabilizer									
Thermolite 31	2.0	---	2.0	---	---	1.0	---	2.0	---
Argus 292	---	2.0	---	2.0	---	---	1.3	---	1.0
Cardinal Clear 11	---	---	---	---	2.0	---	---	---	---
Lubricant									
Ca Stearate	0.8	0.8	0.8	0.8	0.8	0.8	0.8	1.0	0.8
Ba Stearate	0.3	0.3	0.3	0.3	0.3	0.3	0.3	---	0.3
Lenco 2770	0.75	0.75	0.75	0.75	0.75	0.85	0.75	---	0.75
Advawax 280	---	---	---	---	---	---	---	1.0	---
Processing Aid									
K120N	3.5	3.5	3.5	3.5	3.5	3.0	3.5	5.0	3.0
Pigment									
TiO_2	1.0	1.0	1.0	1.0	1.0	0.5	1.0	1.0	0.5
Blue	0.1	0.1	0.1	0.1	0.1	0.05	0.1	0.1	0.05
Anti Plate-Out									
(if necessary) Hovacite or Superfloss	0.033	0.033	0.033	0.033	0.033	0.033	0.033	0.033	0.033

TRADE SECRET
J-RN 83