CODE QC-16-B LOT E1340

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
50	68	3400		
	STUMP	Lump 3525#		

TOTAL NET WT. 3400 PKG. N-CODE 1000

PROD. SPVR.	DATE	WHSE. OPER.
[illegible]	5 15 81	

92
245

CC 01 CODE YC-16-B PKG. 93

→ MAY -0-81-E-1340

EST. WGT. 3130 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES	APPROVED BY
	(A) YC-16-B	A.C 4-7-75
		JFH 5-5-75
		DCG 5-14-75
	TYPED BY	

MAKING NOTES

REMARKS

NAME: MOLYBDATE ORANGE EC NON-BLEEDING

INSTRUCTIONS — PRESSING — RECORD

VAT			245			
DATE			5-13			
TIME			2:10PM			
RELEASED BY			JWB			
PRESS	91	92	93	2	25	
NO. OF CAKES	42	32	32	32	32	

PRESS
WASH TO 2000 AGITATION OHMS
TEST AFTER 2 HOURS WITH 35-75 F WATER
LOAD ON 4 CARS

TDS

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	5P				
CAKES USED	132				
WATER ON	9PM				
HRS. WASHED	2½				
OHMS	2500				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	5				

EXPLAIN LOSSES

SAMPLES
DELIVER TO

SAMPLED BY RELEASED BY BH

— DRYING —

DRY 16 HOURS AT 220 F

LUMP: - OK - WET - SALTS - CONTAMINATED
DRYER SECTIONS USED:
Color appears dry heaters released

ADDITIONAL DRYING HOURS REQUIRED 1

NO. DRUMS 12

SAMPLES
DELIVER TO

NO. CARS PULLED LUMP WGT. 3525
SAMPLED BY RELEASED BY PH

— GRINDING —

MICROATOMIZE
SET ROOF GATE AT 5 INCHES AIR FLOW
MAGNEHELIC READING ON ATOMIZER PANEL 1.0"

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV
DELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

DUP050096141

1340
41
16

0.00 *

3.40 +
0.12 -
3.37 +
0.12 -
3.30 +
0.12 -
3.28 +
0.12 -
3.21 +
0.12 -
3.07 +
0.12 -
18.91 *

1340
41
16

0.00 *

3.22 +
0.12 -
3.44 +
0.12 -
3.17 +
0.12 -
3.25 +
0.12 -
2.98 +
0.12 -
1.00 +
0.12 -
16.34 *

18.91 +
16.34 +
35.25 *

DUP050096142